



敬业钢铁有限公司
Jingye Iron and Steel Co.,Ltd.
质量证明书
Mill Test Certificate



中国认可
产品
PRODUCT
CNAS C162-P

订货单位 Customer	敬业钢铁有限公司	产品名称 Commodity	钢筋混凝土用钢：热轧光圆钢筋 STEEL REINFORCED CONCRETE: HOT ROLLED RIBBED BARS		
收货单位 Consignee	敬业钢铁有限公司	装车作业单编号 Loading Job No.	LT260806035	质保书编号 Certificate No.	260806W00201
执行标准 Standard	GB 1499.1-2024	签发日期 Date of Issue	2026/08/06	合同编号 Contract No.	NW260806011
牌号 Grade	HPB300	车号 Truck No.		发货日期 Date of Delivery	2026/08/06
生产许可证编号 Permission No.	(冀) XK05-001-00001	交货状态 Delivery State	热轧 Hot rolled		

项次 ITEM No.	轧制批号 LOT No.	炉号 HEAT No.	规格 DIMENSION (mm)	件数 PCS	重量 Weight (t)	熔炼成分 Cast Analysis%									拉伸试验 x1 TENSILE TEST		最大 力总 延伸 Agt%	R°m/ R°e1	R°e1 /Re1	弯曲 试验	反弯 试验			
						C	Si	Mn	P	S	V	Cr	Nb	Ceq	屈服 ReLY.S	抗拉 RmT.S								
						- 2 X10	- 2 X10	- 2 X10	- 3 X10	- 3 X10	- 3 X10	- 3 X10	- 3 X10	- 2 X10	MPa	MPa								
001	X326080015028	26501225	Φ6	26	55.35	21	18	82	32	16	3	50	1	38	350	550	14.6	1.50	1.09	合格	合格			
																							合格	合格
																							合格	合格

合计(TOTAL)	26	55.35																		
-----------	----	-------	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--

注释 NOTE	Y. S屈服强度=Yield Strength T. S抗拉强度=Tensile Strength 最大力总延伸Agt%=Total elongation at maximum force. R ^o m/R ^o e1=Tensile/yield strength ratio										R ^o e1/Re1=Yield Strength / Globe Standard's Yield Strength 弯曲试验=Bending Test 弯曲角度=Angle Of Bend 反弯试验=Rebend Test									
------------	--	--	--	--	--	--	--	--	--	--	---	--	--	--	--	--	--	--	--	--

备注 REMARK	本产品N含量能保证，重量偏差、钢筋尺寸、表面质量、金相组织均符合标准规定。请用户按产品批号验收，如有质量异议请填写好质量异议函，并将实物妥善保管好，切勿动用。 THE N CONTENT OF THIS PRODUCT CAN BE GUARANTEED, AND THE WEIGHT DEVIATION, STEEL BAR SIZE, SURFACE QUALITY, AND METALLOGRAPHIC STRUCTURE ALL MEET THE STANDARD REQUIREMENTS. PLEASE HAVE THE USER INSPECT THE PRODUCT ACCORDING TO THE BATCH NUMBER. IF THERE ARE ANY QUALITY OBJECTIONS, PLEASE FILL OUT THE QUALITY OBJECTION LETTER AND KEEP THE PHYSICAL ITEM PROPERLY. DO NOT USE IT.										曹建虎 CAO JIANHU									
											计量质检部部长 General manager, department of product testing									

