



WC-788 A/B

WATER CLEAR RIGID 84 SHORE D

URETHANE CASTING SYSTEM

PRODUCT DESCRIPTION:

WC-788 A/B is an impact resistant, rigid, 84 Shore D aliphatic polyurethane that is commonly used to make clear or tinted castings of all kinds. Note: WC-788 A/B requires post-curing. Thin section casts, less than 1/2" thick, may require in mold post-curing. See post-cure instructions on page 2.

PRODUCT HIGHLIGHTS:

- Colorless with exceptional clarity
- Excellent impact strength
- 15 minute standard working time with six additional work speeds available
- No odor
- Good weatherability, non-yellowing all aliphatic
- Excellent heat resistance

PHYSICAL PROPERTIES:

Hardness, Shore D ASTM D-2240.....	84 ± 2
Density (g/cc) ASTM D-792.....	1.1
Cubic Inches Per Pound	26.2
Color/Appearance.....	Water clear/colorless
Tensile Strength, (psi) ASTM D-638.....	8,300
Tensile Modulus, (psi) ASTM D-638.....	2.7 x 10 ⁵
Elongation, (%) ASTM D-638.....	20
Flexural Strength, (psi) ASTM D-790.....	11,200
Flexural Modulus, (psi) ASTM D-790	3.0 x 10 ⁵
Shrinkage, (in./in.) linear (12"x 1/2 "x 1/2 ")	0.006
Izod Impact, notched (ft.-lb./in.) ASTM D-256	1.1
Heat Deflection Temperature, (@ 66 psi) ASTM D-648.....	175°F (79°C)
Index of Refraction ASTM D-542.....	1.49

HANDLING PROPERTIES:

Mix Ratio (by weight):

Part A	100 parts by weight
Part B	75 parts by weight

Mix Ratio (by volume):

Part A	100 parts by volume
Part B	78 parts by volume

Viscosity, (cps) @ 77°F (25°C) ASTM D-2393:

Part A	650 ± 50
Part B	750
Mixed.....	650 ± 50

HANDLING PROPERTIES (cont'd):

Specific Gravity:

Part A 1.08

Part B 1.04

Work Time (100g mass) @ 77°F (25°C)..... 15 - 20 minutes*

Demold Time @ 77°F (25°C)..... 16 - 24 hours

*The 15-20 minute work time is the standard in-stock product. Products with 5, 30, 60, 90, 180 and 240 minute work times are available on a special order basis.

CURE SCHEDULE/HEAT CURING:

Most of the physical properties can be achieved in 5-7 days at ambient temperature, 77°F (25°C). In order to achieve maximum physical properties, a post cure with heat is required. BJB recommends 24 hours at ambient temperature, 77°F (25°C), followed by 16 hours at 180°F (82°C). Support of the part may be required to prevent part deformation during heat cure.

NOTE:

The cure will be inhibited if cast against a tin catalyzed silicone RTV.

STORAGE AND HANDLING:

All materials should be kept in tightly closed containers out of contact with moist air. Stored under these conditions at temperatures of 60° - 80°F (16° - 27°C), the shelf life is 6 months from date of shipment. Part B may turn hazy or partially freeze below 65°F (18°C) storage. Warming to 80° - 90°F (27° - 32°C) will return product to a clear state.

PACKAGING:

Gallon Kits..... 8 lbs. A, 6 lbs. B

5 Gallon Kits..... 40 lbs. A, 30 lbs. B

55 Gallon Drum Kits 400 lbs. A, 300 lbs. B

SAFETY PRECAUTIONS:

Avoid contact with skin using protective gloves and protective clothing. Repeated or prolonged contact on the skin may cause an allergic reaction. Eye protection is extremely important. Always use approved safety glasses or goggles when handling this product. Use in well-ventilated areas. Avoid breathing vapors. If exposures cannot be kept at a minimum, a respirator may be necessary in addition to ventilation. The use of a positive pressure air supplied respirator is mandatory when airborne isocyanate concentrations are "not known" or exceeds OSHA'S TWA of 0.005 ppm. Air purifying, organic cartridge type respirators are not generally recommended to use when handling this material without implementation of an end of life service program. Observe OSHA regulations for respirator use (29 CFR 1910.134). Employers are responsible for selecting the correct respirator for each situation.

IF CONTACT OCCURS:

Skin: Immediately wash with soap and water. Remove contaminated clothing and launder before reuse. It is *not* recommended to remove resin from skin with solvents. Solvents only increase contact and dry skin. Seek qualified medical attention if allergic reactions occur.

Eyes: Immediately flush with water for at least 15 minutes. Call a physician.

Ingestion: If swallowed, call a physician immediately. Remove stomach contents by gastric suction or induce vomiting only as directed by medical personnel. Never give anything by mouth to an unconscious person.

Refer to the Material Safety Data Sheet before using this product.