


REPORT NUMBER: GZHT02957549

Sample Photo



TEST REPORT

检测检验报告

Number: GZHT02957549
报告号

Applicant: GUANGZHOU EARTHING HEALTH TECHNOLOGY
委托单位:
Address: 广州接地宝健康科技有限公司
地址: 广州市天河区黄村北路 6 号 D 区 D18 之 B209 房
Attn: 施宇霖
联系人

Date: Jan 14, 2025
日期:

Sample Description:

One (1) Group Of Submitted Sample Said To Be Woven Fabric In White.

样品描述 样品数量: 1 组
样品规格: 客户认定为梭织布, 白色。

Applicant's Provided Care Instruction/Label: -

申请人所提供之水洗标签

Date Received : 2025-01-06

接收日期

Date Tests Started : 2025-01-06

测试开始日期

批准
Approved by

刘慧利
高级经理

李鹏宝
高级技术专家

WY/qiqixu



第 1 页 共 9 页

Intertek Testing Services Shenzhen Ltd. Guangzhou Branch

Room 401/501/601/801/901/1003, No. 8 East BaoYing Road, Huangpu District, Guangzhou, China

深圳天祥质量技术服务有限公司广州分公司

广州市黄埔区保盈东路 8 号 401 房、501 房、601 房、801 房、901 房、1003 房

Tel: +86 20 2820 9118 E-mail: textile.gz@intertek.com Postcode: 510730

www.intertek.com

TEST REPORT
检测检验报告

Number: GZHT02957549
报告号

Brand Name : EARTHED
品牌
Manufacturer's Name : 广州接地宝健康科技有限公司
生产商
Reference Standard : GB 31701-2015 Safety technical code for infants and children textile products
参考标准 GB 31701-2015 《婴幼儿及儿童纺织产品安全技术规范》
Textile Products for Infants
婴幼儿用品
Remark : Sample Description/样品描述: Cotton Silver Fiber
备注 Fiber Content/成分: 棉+银纤维
Yarn Content/纱支: 40s+140D 银纤维 x40s+140D 银纤维
End Uses/最终用途: 家纺用品
Age Limit/年龄段 (婴儿儿童产品): 3 岁及以下
Sweater Produce/毛衣类产品: 精梳

批准
Approved by

刘慧利
高级经理

李鹏宝
高级技术专家

WY/qiqixu



第 2 页 共 9 页

TEST REPORT

检测检验报告

Number: GZHT02957549

报告号

Conclusion:

结论

Fibre Analysis (纤维含量)	*1
Formaldehyde Content(甲醛含量)	M
pH Value(pH 值)	M
Presence Of Odor(异味)	M
Colour Fastness To Rubbing(耐摩擦色牢度)	M
Colour Fastness To Perspiration(耐汗渍色牢度)	M
Colour Fastness To Water(耐水色牢度)	M
Colour Fastness To Saliva(耐唾液色牢度)	M
Azo Dyes(可分解致癌芳香胺染料)	M

Note: M = Meet Standard's Requirement
C = Conform To The Declared Fibre Content
= No Comment

F = Below Standard's Requirement
* = See Remark
N/A = Not Applicable

备注: M = 符合标准要求
C = 符合公告的成分内容
= 无评语

F = 不符合标准要求
* = 看注解
N/A = 不适用

*1 See test result / 见测试结果

Test Conducted:
测试内容:

- 1.As Requested By The Applicant, For Details Refer To Attached Page (S)
以下测试依据申请人所要求进行,具体内容参见附页
- 2.All the tested item are tested under the standard condition (except for indication).
本报告中检测项目均在相应标准规定的环境条件下进行(有注明的除外)。

Remark:
备注:

- 1.The Chinese version of this test report is the standard one; the English version is only for reference.
此报告以中文为主英文仅作参考。
- 2.The report is valid with commission test only for the test samples in the case of delivering samples by clients. No copy test report is valid without original special stamp of the test body.
检验仅对检测样负责,复印件未重新加盖红色检验专用章无效。

批准
Approved by

刘慧利
高级经理

李鹏宝
高级技术专家

WY/qiqixu



第 3 页 共 9 页

Intertek Testing Services Shenzhen Ltd.Guangzhou Branch

Room 401/501/601/801/1003, No. 8, East BaoYing Road, Huangpu District, Guangzhou, China

深圳天祥质量技术服务有限公司广州分公司

广州市黄埔区保盈东路 8 号 401 房、501 房、601 房、801 房、901 房、1003 房

Tel: +86 20 2820 9118 E-mail: textile.gz@intertek.com Postcode: 510730

www.intertek.com

Number: GZHT02957549
报告号:

- 1 Fibre Analysis (FZ/T 01057.1~4-2007, GB/T 2910.1-2009):
纤维含量 (FZ/T 01057.1~4-2007, GB/T 2910.1-2009):

Marked
备注

=====

Based On Moisture Regain Weight
根据公定回潮率重量

95.9% Cotton 4.1% Metallized Fibres #
95.9% 棉 4.1% 金属镀膜纤维

-

Remark : Moisture Regain Based On GB/T 9994-2018
备注: 公定回潮率 (参照 GB/T 9994-2018)
Metallized Fibres was found to be Polyamide base
金属镀膜纤维以锦纶为底

- 2 Formaldehyde Content (GB/T 2912.1-2009):
甲醛含量 (GB/T 2912.1-2009):

Requirement
要求

=====

Not Detectable
未检出

≤ 20 mg/kg

Remark: Detection Limit = 20 mg/kg
备注: 检出限 = 20 mg/kg

- 3 pH Value (GB/T 7573-2009, KCl):
pH 值 (GB/T 7573-2009, KCl):

Requirement
要求

=====

6.3

4.0-7.5

Number: GZHT02957549

报告号:

- 4 Presence Of Odor (GB 18401-2010 Section 6.7):
异味 (GB 18401-2010, 6.7):

Negative
无异味

Requirement
要求

=====

Negative
无异味

- 5 Colour Fastness To Rubbing As Received (GB/T 3920-2008):
耐摩擦色牢度 (GB/T 3920-2008):

Dry
干
Wet
湿

4-5
4-5

Requirement
要求

=====

Dark Shade
深色
≥ 4

≥ 2-3

Remark : Unit : Grade
备注: 单位: 级

Number: GZHT02957549
报告号:

6 Colour Fastness To Perspiration (GB/T 3922-2013):
耐汗渍色牢度 (GB/T 3922-2013):

			Requirement 要求 =====
	Acid 酸	Alkaline 碱	
Colour Change 颜色变化	4-5	4-5	≥ 3-4
Colour Staining 沾色			≥ 3-4
-Cotton 棉	4-5	4-5	
-Wool 羊毛	4-5	4-5	

Remark : Unit : Grade
备注: 单位: 级

7 Colour Fastness To Water (GB/T 5713-2013):
耐水色牢度 (GB/T 5713-2013):

		Requirement 要求 =====
Colour Change 颜色变化	4-5	≥ 3-4
Colour Staining 沾色		≥ 3-4
-Cotton 棉	4-5	
-Wool 羊毛	4-5	

Remark : Unit : Grade
备注: 单位: 级

Number: GZHT02957549

报告号:

8 Colour Fastness To Saliva (GB/T 18886-2019):
耐唾液色牢度 (GB/T 18886-2019):

		Requirement 要求 =====
Colour Change 颜色变化	4-5	≥ 4
Colour Staining 沾色		≥ 4
-Cotton 棉	4-5	
-Wool 羊毛	4-5	

Remark : Unit : Grade

备注: 单位: 级

9 Detection of Amines Content in Dyestuffs

可分解致癌芳香胺染料

As per GB 18401-2010, GB/T 17592-2011 Were Used, Amines Content in Dyestuffs Were Detected by Gas Chromatography - Mass Spectrometry (GC-MS).

根据 GB18401-2010 的要求, 采用测试方法: GB/T 17592-2011, 可分解致癌芳香胺染料使用气相色谱-质谱联用仪 (GC-MS) 检测。

	<u>Forbidden Amine</u> 禁用芳香胺	<u>CAS No.</u> 化学文摘编号	<u>Result (mg/kg)</u> 结果 (mg/kg)	<u>Requirement (mg/kg)</u> 要求 (mg/kg)
			(1)	
1	4-Aminodiphenyl 4-氨基联苯	92-67-1	ND	≤ 20
2	Benzidine 联苯胺	92-87-5	ND	≤ 20
3	4-Chloro-O-Toluidine 4-氯邻甲苯胺	95-69-2	ND	≤ 20
4	2-Naphthylamine 2-萘胺	91-59-8	ND	≤ 20

qiqixu/WY

第 7 页 共 9 页

Intertek Testing Services Shenzhen Ltd. Guangzhou Branch

Room 401/501/601/801/901/1003, No. 8, East BaoYing Road, Huangpu District, Guangzhou, China

深圳天祥质量技术服务有限公司广州分公司

广州市黄埔区保盈东路 8 号 401 房、501 房、601 房、801 房、901 房、1003 房

Tel: +86 20 2820 9118 E-mail: textile_gz@intertek.com Postcode: 510730

www.intertek.com

LENZH
务有
★
测专用
10)

TEST REPORT

检测检验报告

Number: GZHT02957549

报告号:

5	O-Aminoazotoluene 邻氨基偶氮甲苯	97-56-3	ND	≤ 20
6	5-nitro-o-toluidine 5-硝基-邻甲苯胺	99-55-8	ND	≤ 20
7	P-Chloroaniline 对氯苯胺	106-47-8	ND	≤ 20
8	2,4-Diaminoanisole 2,4-二氨基苯甲醚	615-05-4	ND	≤ 20
9	4,4'- Diaminodiphenylmethane 4,4'-二氨基二苯甲烷	101-77-9	ND	≤ 20
10	3,3'-Dichlorobenzidine 3,3'-二氯联苯胺	91-94-1	ND	≤ 20
11	3,3'-Dimethoxybenzidine 3,3'-二甲氧基联苯胺	119-90-4	ND	≤ 20
12	3,3'-Dimethylbenzidine 3,3'-二甲基联苯胺	119-93-7	ND	≤ 20
13	3,3'-Dimethyl- 4,4'diaminodiphenylmeth ane 3,3'-二甲基-4,4'-二氨基 二苯甲烷	838-88-0	ND	≤ 20
14	P-Cresidine 2-甲氧基-5-甲基苯胺	120-71-8	ND	≤ 20
15	4,4'-Methylene-Bis(2- Chloroaniline) 4,4'-亚甲基-二-(2-氯苯 胺)	101-14-4	ND	≤ 20
16	4,4'-Oxydianiline 4,4'-二氨基二苯醚	101-80-4	ND	≤ 20
17	4,4'-Thiodianiline 4,4'-二氨基二苯硫醚	139-65-1	ND	≤ 20
18	O-Toluidine 邻甲苯胺	95-53-4	ND	≤ 20
19	2,4-Toluylenediamine 2,4-二氨基甲苯	95-80-7	ND	≤ 20

qiqixu/WY

第 8 页 共 9 页

Intertek Testing Services Shenzhen Ltd. Guangzhou Branch

Room 401/501/601/801/901/1003, No. 8, East BaoYing Road, Huangpu District, Guangzhou, China

深圳天祥质量技术服务有限公司广州分公司

广州市黄埔区保盈东路 8 号 401 房、501 房、601 房、801 房、901 房、1003 房

Tel: +86 20 2820 9118 E-mail: textile.gz@intertek.com Postcode: 510730

www.intertek.com

TEST REPORT

检测检验报告



Number: GZHT02957549
报告号:

20	2,4,5-Trimethylaniline 2,4,5-三甲基苯胺	137-17-7	ND	≤ 20
21	O-Anisidine 邻氨基苯甲醚	90-04-0	ND	≤ 20
22	4-Aminoazobenzene 4-氨基偶氮苯	60-09-3	ND	≤ 20
23	2,4-Xylidine 2,4-二甲基苯胺	95-68-1	ND	≤ 20
24	2,6-Xylidine 2,6-二甲基苯胺	87-62-7	ND	≤ 20

Remark 备注: mg/kg = 毫克/千克
Detection Limit = 5 mg/kg
检出限 = 5 mg/kg
ND = Not Detected
ND = 未检出

Tested Component(s):

(1) White/taupe woven fabric 白色/灰褐色梭织布

End of Report/报告结束

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. No copy of the test report(except for full text copy) shall be made without the written approval by Intertek.

本报告仅基于申请人的指示及/或申请人提供的信息和材料而作出,不应视为采取任何行动的建议。关于本报告, Intertek 不对客户以外的任何人负有谨慎责任或其他责任, Intertek 对客户也只在向其向申请人提供服务的条件条款有明确规定的范围承担责任。Intertek 不就本报告作出除前述条件条款范围之外的任何明示或隐含形式的担保或陈述。Intertek 致力于在勤勉细致的基础上进行审核, 不对因本报告引起的或与本报告有关的任何损失承担任何责任, 包括合同、侵权、法规或其它责任, 除非诉讼结果显示为因 Intertek 严重疏忽或故意的不当行为而造成。未经批准, 本报告不得部分复制, 全文复制除外。

qiqixu/WY

第 9 页 共 9 页

Intertek Testing Services Shenzhen Ltd. Guangzhou Branch

Room 401/501/601/801/901/1003, No. 8, East BaoYing Road, Huangpu District, Guangzhou, China

深圳天祥质量技术服务有限公司广州分公司

广州市黄埔区保盈东路 8 号 401 房、501 房、601 房、801 房、901 房、1003 房

Tel: +86 20 2820 9118 E-mail: textile_gz@intertek.com Postcode: 510730

www.intertek.com