



Anhui Moon Technology Co., Ltd.

Room 449, Building 3, Industrial Park, 1151 Yanan South Road, Bengshan District, Anhui China

POST CODE: 233030


Email:echo@ahmoontech.com

TEL,FAX: +86-552-2079969

TDS/F823

1H,1H,2H,2H- perfluorooctane triethoxysilane

Structureal formula:



Technical Index

Chemical Name: 1H,1H,2H,2H- perfluorooctane triethoxysilane

Cas No.:51851-37-7

EINECS No.:257-473-3

MF:C14H19F13O3Si

Appearance:Colorless clear liquid

Refractive index :1.3400~1.3500

Purity:97%

Product Description:

It is releases low molecular weight alcohols after hydrolysis, resulting in active silanols that can chemically bond with hydroxyl, carboxyl, and oxygen-containing groups in many inorganic and organic substrates, forming self-assembled single-molecule fluorosilicone film layers on the surface of inorganic materials.

Use:

F823 is a raw material in the field of anti-reflection coating, anti-stick coating and anti-fouling coating.

Packing:

210L steel drum:

200kg/ drum

25L Plastic drum:

25kg/ drum