



Anhui Moon Technology Co., Ltd.

Room 449, Building 3, Industrial Park, 1151 Yanan South Road, Bengshan District, Anhui China

POST CODE: 233030

Email: echo@ahmoontech.com


TEL, FAX: +86-552-2079969

Technic data sheet

MOON-V171

Ethenyltrimethoxysilan

Formula:



Foreign corresponding brand:

General chemistry	Dow corning	ShinEtsu	Degussa	CHISSO
A-171	Z-6300	KBM-1003	VTMO	N.A

Technical indicators

Brand:	MOON-V171
Chemical name:	Ethenyltrimethoxysilan
CAS no. :	2768-02-7
EINECS no. :	220-449-8
Molecular formula:	C ₈ H ₁₈ O ₃ Si
Appearance:	Colorless transparent liquid
Density (ρ ₂₀ , g/cm ³):	0.9718 + / - 0.0050
Refractive index (n _{25D}) :	1.3925 + / - 0.0050
Content	98%

USES:

1. It is used to prepare moisture cured silane crosslinked polymer, such as silane crosslinked polyethylene (XLPE), so that thermoplastic resin and thermosetting resin have better heat resistance, acid and alkaline resistance and better mechanical strength.
2. It is used to prepare organosilicon modified acrylic emulsion, organosilicon modified butadiene latex and other organosilicon modified polymers to improve the hydrophobicity and adhesion of polymers.
3. It is used to improve the binding force, compatibility and adhesion of inorganic powder materials to high polymer.

Packing:

200L iron drum: 190kg/ drum

1000L IBC drum: 950kg/ drum