



Anhui MOON Technology Co., Ltd.

Room 449, Building 3, Industrial Park, 1151 Yanan South Road, Bengbu City, Anhui Province, China
TEL, FAX: +86-552-2079969 POST CODE: 233000


Product information

MOON-D90

Vinyltris(methylethyl ketoxime)silane

Product description

Structural formula:



Empirical formula: $\text{C}_{14}\text{H}_{27}\text{N}_3\text{O}_3\text{Si}$

Molecular weight: 313.5

CAS No.: 2224-33-1

Chemical name:

Vinyltris(methylethylketoxime)silane

Properties and reactivity

MOON-D90 is a clear and almost colorless fluid with a typical smell (MEKO).
It readily hydrolyzes upon contact with moisture.

Technical data

Typical characteristics	Value
Appearance	Clear to light yellow transparent liquid
Purity	$\geq 90.0\%$
Density at 25°C	0.99g/ml
Boiling point at 760mmHg	300°C
Flash point (closed cup)	106°C
Refractive index (25°C)	1.4635



Anhui MOON Technology Co., Ltd.

Room 449, Building 3, Industrial Park, 1151 Yanan South Road, Bengbu City, Anhui Province, China
TEL, FAX: +86-552-2079969 POST CODE: 233000

Application and performance

MOON-D90 is used as a neutral curing agent in silicone sealant formulations. In most cases MOON-D90 is used in combination with methyloxime silane. Compared to formulations based on methyloxime silanes only, the use of combinations containing methyl- and vinyloxime silanes leads to a shorter skin formation time of the silicone sealant without a reduction of the curing time. The ability of the sealant to withstand stress early, required for a certain elasticity and tear resistance, is achieved.

Product safety, handling and storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage condition required. The “Best use before end” date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Packaging

Information on available container sizes is obtainable from **MOON TECH** supplier.

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.