


**Product information****D-15**

Ethyl tri acetoxysilane

Product description

Structural formula:

Empirical formula: C₈H₁₄O₆Si

Molecular weight: 234.28

CAS No.: 17689-77-9

Chemical name: Ethyl tri acetoxysilane

Properties

D-15 is a clear to yellowish liquid with low-viscosity and acrid odor of acetic acid (vinegar).

D-15 catalyst has been specifically formulated to remain liquid at temperatures above 5°C to permit easier handling in most applications.

Technical data

Typical characteristics	Value
Appearance	clear to light yellow transparent liquid
Purity	≥90%
Density at 25°C	1.14g/ml
Boiling point(760mmHg)	216.1 °C
Flash point(close cup)	96.7°C
Refractive index (20°C)	1.411

Note: the above data are for reference only, can not be used as a technical specification

Reactivity

D-15 readily hydrolyzes upon contact with moisture. Hydrolyzed with water without catalyst at room temperature. The hydrolysis activity was lower than D-10.

Application and performance

D-15 is transported from the production site as the parent silane to formulators. Generally, D-15 is used as a cross-linker at 3% to 5%.

D-15 is often the main crosslinker of choice for silicone sealants and can be used by itself or in combination with other acetoxysilane to provide the sealant with targeted properties (such as desired cure rate, adhesion, etc).

The formulation process is similar to that of conventional acetoxysilane systems. In the first step, polymer and silicone oil are mixed and degassed. After that, Crosslinker D-15 are added and homogenized. After mixing in Crosslinker D-15, mixing should continue for another 15 minutes. After that, the fumed silica, further fillers, pigments are added and homogenized. At the end, Catalyst D-70 is added and mixed in vacuum.



Product safety, handling and storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage condition required. The “Best use before end” date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Packaging

Information on available container sizes is obtainable from **HUBEI BLUESKY** supplier.

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.

HUBEI BLUESKY NEW MATERIAL INC.
NO.8 CHEMICAL INDUSTRY PARK ECONOMIC
DEVELOPMENT ZONE XIANTAO ,HUBEI ,CHINA
TEL:0086-728-3254088 Fax:0086-728-3253808
mail:wulin@blueskychemical.com
Website: www.blueskychemical.com