



Methyl mixed with fatty crosslinkers

Product Information

D-31 (MOS/TOS=80/20)

Methyl mixed with fatty crosslinkers

Molecular formula: $C_{13}H_{27}N_3O_3Si$ $C_{16}H_{32}N_4O_4Si$

Molecular weight: 301.46 372.54

CAS No. : N.A

Chemical name: methyl-tributyl fatty silicon Kang/tetrabutyl-fatty silicon Kang mixture

Product Features

Colorless or light yellow transparent, with fatty (Dingli) flavor liquid.

Physical and chemical data

Properties	Numerical value
appearance	Colorless or light yellow clear liquid
MOS:TOS	MOS II 75.0% TOS II 15.0%
Density 25 knots	0.98 g/ml
Boiling point 760mmHg	>300 knots
Closed cup flash point	106.7 knots
Refractive index 25 knots	1.451

Note: The above data is for reference only and cannot be formulated as technical specifications

Reaction properties

D-31 is a kang base tri-butyated silicon kang mixture. Tri-butyl is hydrolyzable, soThe product is easily hydrolyzed by moisture (contact with water).

In the presence of organotin catalyst, D-31 can react with polysiloxone containing light base to form cross-linked silicone rubber.

Product Application

Deketoxime type single component room temperature vulcanized silicone rubber crosslinking agent. D-31 can be used as a crosslinking agent for single component neutral curing silicone sealant. It is often the main crosslinker of choice for deoxime-type silicone sealants. It can be used alone or in combination with other oxime-silanes to provide desired properties (such as cure rate, bond, etc.).

Precautions

In the actual storage (seal is not opened) process, when the ambient temperature is lower than 15 ° C, there may be crystallization phenomenon at the bottom of the barrel, check whether there is crystallization before use. If crystallization has occurred, do not use directly, it is recommended to use after drying. It may turn yellow when stored above 35°C for a long time. Please store it in a suitable warehouse and prepare the goods properly.

Product safety, handling and storage

Before using the product, you should carefully read the latest product safety technical information and toxicity data of the product to And the correct storage and use information of the product. The container should be sealed after opening to prevent water vapor from entering the hydrolysis. The effective time of the product is indicated on the label. After this time, does not mean that the product has It can not be used again, and can still be used after the performance test confirms that it is qualified.

Packaging

The size of the available containers can be checked with Moon Tech.

This product information, as well as all technical advice, is based on our current level of experience and knowledge. We accept no liability whatsoever, including for known third party intellectual property rights. In particular, we do not make any guarantee or warranty in a legal sense as to the nature of the Products. We reserve the right to make any changes to the product information due to technological progress or further development. The customer carefully tests and inspects the product itself. This description of the nature of the product should also be verified by the Customer through professional testing. References to grades used by other companies are neither recommendations nor exclusions from the availability of similar products.

Anhui Moon Technology Co., Ltd.'s sole warranty is that the products meet the Anhui Moon Technology Co., Ltd. sales specifications at the time of shipment.

Your only remedy for breach of Warranty by Anhui Moon Technology Co., Ltd. is a refund of the purchase price or replacement of any product that does not comply with the Warranty.