




Product information

D-130 (SI28)

Tetraethylsilane, Tetraethyl orthosilicate

Product description

Structural formula:



Empirical formula: $\text{C}_8\text{H}_{20}\text{O}_4\text{Si}$

Molecular weight: 208.33

CAS No.: 78-10-4

Chemical name: Tetraethylsilane, Tetraethyl orthosilicate

Properties

Good penetration, due to small molecular size.
Inorganic binder, UV stable.
Used for sol-gel processes in combination with other alkylsilanes such as D-150 Silane.

Reactivity

Tetraethyl orthosilicate (TEOS) will react with moisture to form a silica-gel like binder and ethanol byproduct which evaporates.

Technical data

Typical characteristics	Value
Appearance	Colorless transparent liquid
Purity	$\geq 98.0\%$
Density at 25°C	0.94g/ml
Boiling point at 760mmHg	168°C
Flash point	46.67°C
Refractive index (20°C)	1.382

Note: the above data are for reference only, can not be used as a technical specification

Application and performance

D-130 (SI28) Silane that can be applied neat, diluted or as part of a formulated product. Applied to natural stones or other construction materials, it forms a silica-gel like binder (SiO_2) that increases the substrate strength. Polymerization of silicone resins for use in paints and other surface modification applications intermediate for sol-gel process. For the manufacture of sealant materials RTV-2, D-130 (SI28) can be used as a cross-linking agent. On glass and plastic lens materials, D-130 (SI28) silane provides a scratch-resistant, hard-coat to the finish.



Anhui Moon Technology Co., Ltd

Room 449, Building 3, Industrial Park, 1151 Yan'an South Road, Bengbu City, Anhui Province, China

TEL, FAX: +86-552-2079969 POST CODE: 233000

Product safety, handling and storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage condition required. The “Best use before end” date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Packaging

25KG foreign trade plastic drum, 180KG internal coated iron drum.

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.