TECHNICAL DATA SHEET

COSMO-POLYURETHANE

ALIPHATIC POLYURETHANE-BASED COATING

Precision-formulated epoxy coatings for demanding environments.

Product Overview

COSMO-POLIURETHANE is a two-component glossy acrylic aliphatic polyurethane finish. It is a product with a high solids content, with a long useful life, provides durable finishes and has good gloss retention. This product provides good resistance to abrasion and chemicals.

Applications

COSMO-POLIURETHANE is applied over a suitable anticorrosive or primer. It is used on metal structures and concrete exposed to industrial environments, as well as on bridges, chemical plants as well as on marine vessels to give a durable finish with good gloss retention. Provides good resistance to abrasion and chemicals.

Technical Especifications

Specification	Characteristic
Solids in Volume	65% ± 2
Colors	WHITE
Finish	Bright
Volatile Content (VOC)	268 g/L
Typical Thickness	2.0 – 3.0 Mils DRY (4.0 – 6.0 Mils WET)
Theoretical Coverage	525.3 sq ft (48.8 m2) / gal at 2 Mils DRY (WITHOUT CONSIDERING LOSSES DUE TO APPLICATION AND TRANSFER OF THE PRODUCT)
Application methods	AIRLESS EQUIPMENT, AIR PRESSURE EQUIPMENT
Storage	1 YEAR IN A FRESH ENVIRONMENT, PART A 6 MONTHS IN A COOL ENVIRONMENT, PART B

Surface Preparation

Remove all residue, oil, dirt, grease, dust, rust, contaminants and excessive moisture present on the surface. Refer to the Application Sheet for detailed information on surface preparation. A summary of the recommended preparation:

Galvanized Steel	• SSPC-SP1 (Solvent Cleaning) • SSPC-SP2 (Hand Tool Cleaning) • SSPC-SP7 (Power Tool Cleaning)
Aluminum	• SSPC-SP1 (Solvent Cleaning)
Concrete and Masonry	
• **by atmosphere** • **by inmersion**	• NACE 6/SSPC-SP13 • NACE 6/SSPC-SP13, Section 4.3.1 or 4.3.2.
Iron and Steel	
• **by atmosphere** • **by inmersion**	• SSPC-SP1, SSPC-SP2, and SSPC-SP6 • SSPC-SP1 and SSPC-SP10 (Near-White Blast Cleaning).
Previously Painted Surfaces	• Consult the COSMOS® Application Guide for specific recommendations.

Product Preparation

• Shake each component (A and B) separately, then mix and homogenize by
• Leave to rest for its induction time: 30 MIN (between 40 – 77 °F / 4.4 - 25 °C); 15MIN (100 °F / 38 °C).
• Then apply COSMO-EPOXY B-81 ANTI-CORROSIVE EPOXY POLYAMIDE BASE.

Drying & Curing Times

Property	54°F / 12°C	77°F / 25°C	100°F / 38°C
Touch Dry	12 hrs	6 hrs	4 hrs
To Handle	36 hours	14 hrs	12 hrs
Final Curing	4 days	3 days	2 days
Interval between coats*	12 hrs – 36 hrs	9 hrs – 24 hrs	6 hrs – 16 hrs

*Repainting times depend on temperature, relative humidity and applied thickness.

Application Methods

© 2026 Cosmos Coatings. All rights reserved.

InfoPeru@CosmosCoatings.com
YouTube · LinkedIn

• MIXING RATIO – 4:1 By volume
• SHELF LIFE OF THE MIXTURE AT 77 °F / 25 °C – 2 hours once the paint is prepared, use it completely. After the useful life, the paint should not be applied. Open containers should not be stored.
• Brush or Roller: Use COSMO-EPOXY E-65 POLYAMIDE EPOXY ENAMEL as it remains after catalyzing. Brush should be made of Nylon/Polyester or Natural Bristle, and the roller should be made of Plush 3/8" (9.53 mm) with a phenolic core.
• Airless Pistol: (i) Nozzle range.015" - .023" (0.381 - 0.584 mm). (ii) Fluid pressure between 2500 - 3000psi. (iii) Dilute whatever is needed up to 10% by volume
• Conventional Gun: (i) DeVilbiss JGA or MBC 510/704/765 pistol or equivalent. (ii) Dilute between 20% – 25%in volume.

Systems Compatibility

(i) COSMO-POLYURETHANE can be used as a finish on properly primed surfaces. (ii) For specific cases, consult our Technical Service. (iii) The paint should be applied at a relative humidity of no more than 85% since the gloss could be affected. Likewise, condensation must be avoided on the surface recently applied with COSMO-POLYURETHANE.

Information on Industry Standards

Additional information about industry standards, terms and abbreviations used in this Technical Data Sheet can be obtained from the following institutions:
1. The Association for Materials Protection and Performance (AMPP) was created when NACE International and SSPC merged in 2021).
2. Occupational Safety and Health Administration (OSHA, created in 1970).

Additional Information

The data in this Technical Data Sheet represent typical values of the product characteristics. It is the user's responsibility to take appropriate measures in order to comply with the requirements established within their industry under current legislation. The information represents a general guide and should not be considered as a guarantee of its properties.

Safety Precautions

(i) COSMO-POLYURETHANE should be used by professional applicators in industrial or marine situations, in accordance with the recommendations provided on this sheet and its container. The product should not be used without reference to its technical data sheet. (ii) All work involving the application and use of this product must be carried out in accordance with applicable Health, Safety and Environmental standards and regulations. (iii) Applicators must take the necessary precautions to prevent COSMO-POLYURETHANE from coming into contact with their skin, eyes, or other parts of the body. (iv) If metal coated with this product is flame welded or cut, dust and vapors will be emitted which will require the use of appropriate personal protective equipment and adequate ventilation. (v) For any questions regarding the use of COSMO-POLYURETHANE, consult our Technical Service.

© 2026 Cosmos Coatings. All rights reserved.
InfoPeru@CosmosCoatings.com
YouTube · LinkedIn