

POLY_FIBER - plan: bench-scale melt-spin line: extruder + spinnerette + quench + winder at the 0.09 kg/d draw (A-M-429) (X-POLY sec3) (sheet-metal cabinet
POLY_FIBER - plan: General tolerance ISO 2768-m unless noted.

Aqueous Solutions (owner) AQS-MFG-POLY_FIBER-PLAN
POLY_FIBER fabrication drawing PLAN (AQS-PLAN-006 M3; graph
Type: fabrication drawing (GA / nozzle orientation / part sheet) Rev ee33864a Issued
Created: flow graph pipeline Approved: not approved (study)
Sheet 1 of 1 AQS-DWG-001