

























| | | ENERAL FABRI | C INFORMATION | | | |
|--------------------------------|-----------------------|-------------------------|---------------|------------------------------|---------|------|
| Quality Name | BONA-A6 | | Design Name | BONA 35 | | |
| End-Use | | | Width (±2cm) | 140 cm (55") Weight 480 gr/m | | |
| Composition | %5 CV %54 PAN %41 PES | | Specials | | | |
| | | PHYSI | CAL TESTS | | | |
| Test | | Standarts | | | Results | |
| Abrasion End | | EN ISO 12947-2 | | | 30000 | |
| Wyzenbeek | | ASTM D4157 | | | | |
| Martindale-Pilling 2.000 Cycle | | EN ISO 12945-2 | | | 4/5 | |
| Brush Pilling | | D3511-99A | | | | |
| Test | | Standarts | | | Warp | Weft |
| Seam Slippage | | EN ISO 13936-2 | | | 2.7 | 3.2 |
| Tear Strength | | EN ISO 13937-3 | | | 325 | 96 |
| Tensile Strength | | EN ISO 13934-1 | | | 2643 | 846 |
| Colour Fastness Rubbing | | EN ISO 105-X12(Dry/Wet) | | | 4 | 3/4 |
| Colour Fastness Light | | EN ISO 105-B04 | | | | |
| | | FLAMMA | BILITY TESTS | | | |
| Test | | Standarts | | | Results | |
| Cigarette Test | | BS 5852 PART 1 SOURCE 0 | | | PASS | |
| Cigarette Test | | EN 1021-1 | | | PASS | |
| Cigarette Test | | CALL 117 | | | PASS | |
| Cigarette Test | | NFPA 260 | | | PASS | |

| REPELLENCY / CLEANABILITY TESTS | | | | | |
|---------------------------------|-----------|---------|--|--|--|
| Test | Standarts | Results | | | |

| | CARE CODES | | |
|-------------|------------------------|-----------------|--|
| Washable | Wash 30°C gentle cycle | | |
| Iron | Low iron at max 110°C | C | |
| Tumble dry | Do not tumble dry | Care symbols | |
| Bleach | Do not bleach | Symbols | |
| Dry clean P | Dry cleanable | | |

