

Rotating Polarization of Laser Light Using a Medium in a Magnetic Field

Ed Lipchus*

Department of Physics, Hampshire College, Amherst, MA, 01002

Jiajun Shi[†]

Department of Physics, Amherst College, Amherst MA, 01002

(Dated: October 21, 2014)

Abstract

As observed by Faraday, when passing light through certain materials, one can change its polarization by applying a magnetic field. Each material has a Verdet Constant, which determines the degree to which the applied magnetic field will alter the polarization angle. the verdet constant doesn't physically determine the magnitude of the shift in polarization. That depends on the nature of the birefringent material through which the light is passing. Try "characterizes" or "measures" In our experiment, we passed a red (650nm) laser beam through a glass rod centered within a solenoid and measured the relative change in angle with respect to a rotating polarizer caused by applying a series of different magnetic fields. was the light from the laser beam polarized or unpolarized? Also, as written, this reads as if the magnetic field caused the 2nd polarizer to rotate We then solved for the Verdet constant of the glass rod using two different mathematical methods and compared the results to the accepted values for the glass. this reads as if you used one measurement method and then came up with two different numerical results. That would be disturbing. You actually used two different experimental methods (which then also required different method to calculate the Verdet constant) Our two methods yielded a v_c of $-20.53 \pm 0.382 \frac{\text{rad}}{\text{m}\cdot\text{T}}$ and $18.67 + 0.504 \frac{\text{rad}}{\text{m}\cdot\text{T}}$, compared with the accepted value of $23 \frac{\text{rad}}{\text{m}\cdot\text{T}}$. note: $20.53 - 18.67 = 1.86$, while $0.38 + 0.50 = 0.88$, so results agree within two standard deviations, if you used standard deviation as your measure of error. I assume you meant a positive value of 20.53 rather than the -20.53 value listed above? this "accepted" value is for a particular material at a particular wavelength, and not actually the same wavelength as you used. I think 670 nm instead of 650? And the Verdet "constant" is wavelength dependent. OK to note that this is close to the value reported by Teachspin for a similar rod at a slightly different wavelength, but what you really need to address here is whether or not *your* two measurements are consistent with each other (and those of your classmates) — or alternatively, within how many standard deviations — and if not, whether one of these might be more susceptible to systematic error.

Comments on Abstract:

1. You should decide on whether you want to call it the Faraday Effect or the Faraday Rotation or the Faraday equation, or if you want to use multiple terms, then define faraday rotation in terms of the faraday effect.
2. Need sentence describing how you used a second polarizer to determine the angle of polar-

ization (or relative angle of polarization, or shift in polarization) of the light from the change in light intensity after it passed through the material

3. Need a sentence or two explaining (1) how you detected the relative intensity of the polarized light by measuring the current output from a photodiode (or more specifically, the voltage drop across a 1 Kohm resistor in series with the photodiode) and (2) that the voltage output was proportional to the light intensity (as verified by experiment), and that (3) unwanted voltage offsets and fluctuations in measured light intensity with changes in room lighting were eliminated using by (square-wave) modulation of the laser output and phase-sensitive detection of the transmitted light at the modulation frequency (lock-in amplifier) or some similar language
4. Your description of the two experiments sounds as if you found two different results for a single mathematical value. To improve the clarity of your description, I suggest briefly distinguishing between what you varied, what you measured, and what you calculated. For example, in the first of your two experiments, you measured the sinusoidal variation of polarized light intensity as a function of polarizer angle for a series of magnetic fields ranging from -x tesla to +y tesla, and from that you determined the magnetic-field-dependent phase shift in polarization (or, if you prefer, the magnetic-field dependent change in polarization angle) upon passage through the glass. In the second experiment, you measured the variation in light intensity at a fixed polarizer angle as a function of magnetic field, and used that to find the shift in polarization induced by the magnetic field.

I. INTRODUCTION

In 1845, Michael Faraday discovered that light and magnetic field interact in medium, in which the latter rotates the light's plane of polarization by an angle linearly proportional to the field, provided that the magnetic field is parallel to the direction of propagation of light. This magneto-optical phenomenon, now called Faraday effect, provided the very first evidence that light and magnetism are connected. In mathematical expression, it writes

$$\phi = VBL(\text{radian}) \quad (1)$$

better would be:

$$\phi = v_c BL$$

or

$$\Delta\phi = v_c BL$$

or

where L is the length of the medium light goes through, and B is the magnetic field. V here is a material-dependent number called *Verdet* constant. Hey! you forgot to define ϕ !

do you mean “Mathematically, we write” or perhaps “Mathematically, it is described by the following formula” (or equivalent)? I don't think the magneto-optical phenomenon is doing the writing. Also, I suggest that you use v_c instead of V to avoid confusion with voltage. L isn't in radians, and if you want to indicate that the angle is in radians (which can often be assumed) it is best to do that within the text. .

To experimentally verify the Faraday equation in our lab, we need to measure the induced polarization of light within a certain transparent material in a magnetic field, and calculate the Verdet constant from the equation, then compare it with the actual Verdet constant specified for our material. you didn't induce polarization, you changed the polarization, or, more precisely, the application of a magnetic field caused the polarization angle to rotate (continuously!) as it passed through a birefringent material We proceed with a laser beam going through a transparent material in a magnetic field, and passing through an adjustable polarizer. The output laser beam is finally collected by a photodiode that indicates the light intensity by generating a voltage that we can measure with a multimeter, linked with a computer to collect data. With each magnetic field setting, we rotate the polarizer and record voltage reading from the photodiode, given that the light intensity is dependent on

the polarizer angle. We expect to see a phase shift in the light intensity across different field settings as the magnetically induced polarization is also dependent on the field. It is worth noting that the Faraday effect shall is a relatively small effect with our lab-strength magnetic field. [many of my comments regarding your abstract are applicable here as well.](#)

We use two approaches to model the Faraday effect. One approach is the direct method, in which we find the phase shift in the light intensity [by doing what? by measuring light intensity versus polarizer angle for the rotatable polarizer? versus relative polarization angle?](#)

and [associate](#) it with the magnetic field [“Associate with magnetic field” is ambiguous. do you mean “as a function of magnetic field?” do you mean “plot the result versus magnetic field to look for the linear behavior predicted in equation 1?” Be more specific here please](#)

. This method gives us the Verdet constant directly from the Faraday equation. Another method, called slope method, utilizes the voltage reading at around 45 degrees from maximum on the polarizer to associate the photodiode voltage with the magnetic field. [why 45 degrees? what’s special about that? more likely you chose a setting that maximized the sensitivity of your detector to small changes in magnetic field, and that happens to be a relative angle of 45 degrees.](#) The first method includes the process of sinusoidal fitting of the data using computer software, while the latter requires mathematical manipulation of the Faraday equation. It is expected that the two methods will yield the same Verdet constant value as they are mathematical equivalent. [they aren’t experimentally equivalent, and the sources of error are different in each case. And if there are systematic errors in the setting of the polarizer angle, then you don’t actually expect the same value \(as \$dV/d\phi\$ is a function of \$\phi\$. the reason you hope for the same value is actually because you are measuring the same material in both cases.](#) The descriptions of these two methods can be found in the analysis section.

II. EXPERIMENT

Before we proceed with the Faraday rotation, we first have to determine the magnetic field used for rotation induction. The lab power supply, Keithley 2230-30-1, generates the currents to create magnetic field within the coil, in our case -3A, -2A, 2A, and 3A for a variety of fields to induce different polarization rotations. We also conduct the experiment with no current inside the coil to better observe the change in polarization with respect to

the original polarization of the laser light.

Determining the magnetic field within the coil requires a Gauss meter and some reference, a ruler in our case, to find the distance between the tip of the Gauss meter and the center of the solenoid. We measure the length of the solenoid and make sure the meter tip is centered inside, then pull it out to determine the magnetic field at each point inside the solenoid. In this step, we only supply 1A to the solenoid, as we know from Ampere's law,

$$B = \mu n I \quad (2)$$

where n stands for turns per unit length, that magnetic field inside the solenoid is linearly proportional to the current, so if we find the magnetic field at a point to be B_1 with 1A current supply, we can say the field would be $2B_1$ for 2A, $3B_1$ for 3A, and so on. The measured magnetic field is

TABLE I. Measuring the Magnetic Field Inside the Solenoid

Distance from Center	Magnetic Field
0	$106.5 \pm 0.1\text{G}$
5.5cm	$100 \pm 0.1\text{G}$
6.4cm	$94.9 \pm 0.1\text{G}$
6.7cm	$90.0 \pm 0.1\text{G}$
7.1cm	$80.0 \pm 0.1\text{G}$
7.2cm	$70.0 \pm 0.5\text{G}$
7.8cm	$50.0 \pm 0.5\text{G}$
8.1cm	$40.5 \pm 0.5\text{G}$
8.4cm	$30.0 \pm 0.5\text{G}$

The next step is to insert the glass rod, which serves as the rotation medium in this experiment, into the solenoid. The length reference is again used to make sure the rod is centered inside the solenoid. The length of the glass rod is $10\text{cm} = 0.1\text{m}$, so each end of the glass rod is 0.05m away from the center. According to the above magnetic field table, the field undergoes a minor change from the center to 0.05m away, namely from $106.5 \pm 0.1\text{G}$ to $100 \pm 0.1\text{G}$, suggesting that we can safely take the average value of the fields at these two points, 103G , as the approximation of the magnetic field within the glass rod.

LaTeX tip

write `$0.05 \rm{\ m}$` rather than `$0.05m$`

so as to get 0.05 m instead of 0.05*m*.

better than that simple average would be weighted average such as $\frac{1}{N} \sum_{x_1=-L/2}^{x_N=L/2} B(x_i)$ for equally spaced data measurements or $\frac{1}{L} \int_{-L/2}^{L/2} B(x)dx$ (if you first fit your data to a smooth function for $B(x)$). The difference between your simple average and these would be particularly important when measuring a liquid sample that extends outside the solenoid. Try plotting your data (with errors) to see if a fit would be productive. It depends in part on whether you have any additional data between 0 and 5.5 cm.

The magnetic fields under 2A and 3A shall be 206G and 309G, respectively. Reversing the sign of the current also reverses the sign of the magnetic field.




FIG. 1. Experiment setup. Drawn not to scale.

The initial angle of the polarizer is the angle that allows maximum light intensity. Calling this zero angle, we rotate the polarizer 5 degrees at a time. To filter out any background noise including multimeter noise, background light, and thermal fluctuations within the photodiode, we use several noise reduction devices:




FIG. 2. Noise reduction procedures. The output voltage goes through a pre-amplifier, then a band-pass filter, and finally a lock-in amplifier to eliminate any thermal fluctuations. The room light interference, a systematic error, is minimized by zeroing the multimeter with the room light on.

need more detail for someone to be able to follow and reproduce your experiment. See my comments on your abstract, many of which apply here as well. We don't know how these instruments were used, or why they helped. example: you haven't mentioned that you square-wave modulated the laser output at a particular frequency (200 Hz? 400 Hz?, 1000 Hz? and used that power modulation as the frequency and phase reference for the lock-in (using it as a phase-sensitive ac voltmeter). Nor have you explained that the band pass filter allows you to select a single harmonic of the square wave signal, transforming the square wave at 400 Hz (?) into a sine wave (at 400 Hz, if first harmonic, or 1200 Hz, if 3rd harmonic, ...). And how does each of these improve your signal to noise?

III. ANALYSIS AND DISCUSSION

After collecting data for all five different currents, those points were plotted and fit using the plot.ly interface (see Fig.3). Given the positive, periodic nature of the photodiode intensity, we used the following as the fit parameter:

$$v_d = v_0 * \cos^2(\theta - \theta_0) \quad (3)$$

The simple multiplication symbol isn't included in equations in scientific publications. Voltage symbols are usually capitalized. There is a special \LaTeX command for trig functions. Try:

$$V_d = V_0 \cos^2(\theta - \theta_0) \quad (4)$$

In this manner, by comparing the phase shift θ_0 for each trial, we can find the relative change in polarization resulting from each magnetic field. For error in relative polarizer

angle, we considered ± 1 degree, however when fitting across all 72 points, their combinations constrained the error by a factor of $\frac{1}{\sqrt{72}}$ for an effective error of ± 0.118 degrees. Error in voltage, and thus in magnetic field, is considered negligible based on the precision and stability of our power supply and volt meter. In all cases, degrees were converted to radian at a factor of $\frac{\pi}{180}$ for calculating the Verdet constant. [for your readership, it is probably helpful to point out that all the equations used are in terms of radians, but it shouldn't be necessary to tell us how you converted from degrees to radians. Anybody who can follow the rest of the paper will surely know the conversion factor\)](#)

With the photodiode voltage, relative polarizer angle, and magnetic field strength data, there are two possible methods for calculating the Verdet constant:

$$v_c = \frac{1}{L} \frac{d\theta}{dB} = \frac{1}{L} \frac{\Delta\theta}{\Delta B} \quad (5)$$

TABLE II. Relative Angle vs Magnetic Field

Phase Shift (deg)	Fit Error Δ	Phase Shift (deg)	Current (A)	Magnetic Field (T)	V_d at 45 deg (V)
-1.690	0.1267	-3.692	-3.000	-0.0309	0.6739
-0.047	0.0950	-2.475	-2.000	-0.0206	0.7067
2.002	0.1219	0.000	0.000	0.000	0.7551
4.534	0.1657	2.532	2.000	0.0206	0.8283
5.471	0.1744	3.469	3.000	0.0309	0.8550




FIG. 3. Voltage read at the photodiode as a function of relative angle between the polarizer and the laser beam, with best fit lines added. Shown above are the values with no magnetic field applied and with those created by running a current of 3Amps and -3Amps through our solenoid, demonstrating an obvious phase shift between them. Photodiode voltage and phase shifts were also measured under the fields created by running a current of 2Amps and of -2Amps through the solenoid.

The first method attempts to solve for the Verdet constant directly by graphing $\delta\theta$ versus δB (see Fig.4). The slope of the linear fit of this line provides $\frac{\delta\theta}{\delta B}$, solving for $v_c = -20.53 \frac{\text{rad}}{\text{m}\cdot\text{T}}$. Error in θ was calculated as the sum in quadrature of our error in measurement - 0.118 degrees - and the error in the linear fit - 2.19 degrees. Neglecting error in B, then $\frac{\delta v_c}{v_c} = \frac{\delta\Delta\theta}{\Delta\theta}$, giving an error of $\pm 0.382 \frac{\text{rad}}{\text{m}\cdot\text{T}}$. Thus the direct method yielded a Verdet constant of $-20.53 \pm 0.382 \frac{\text{rad}}{\text{m}\cdot\text{T}}$.

the Verdet coefficient should be expressed as a positive quantity (like the speed of light in a particular material). It is understood from Eq. (1) that reversing the direction of the magnetic field (and hence the sign of B or direction of ΔB) will change the sign of $\Delta\phi$.

The second method, referred to as the slope method, compares the photodiode voltage




FIG. 4. Photodiode voltage as a function of magnetic field at a relative polarizer angle of 45 degrees. As an error in either direction of angle would reduce voltage, only down error bars are considered. To get the error in $\Delta V/\Delta B$, the difference between the best fit slope and the largest and smallest possible fit slopes are calculated.

to the magnetic field strength instead with the following relation:

$$\frac{dV_d}{dB} = \frac{dV_d}{d\theta} \frac{d\theta}{dB} = v_c L \frac{dV_d}{d\theta} \quad (6)$$

From the Verdet equation, we were able to replace the unknown $\frac{d\theta}{dB}$ with the Verdet constant times the length of the glass rod. We can further reduce this equation if we carefully choose a single point at which to analyze this expression. Being a $\cos^2(\theta)$ function, the derivative

$\frac{\delta V_d}{\delta \theta}$ simplifies very nicely at $\frac{\pi}{4}$ as follows:

$$\frac{dV}{d\theta} = -2v_0 \cos(\theta) \sin(\theta) = -v_0 \sin(2\theta) \quad (7)$$

$$\left. \frac{dV}{d\theta} \right|_{\frac{\pi}{4}} = -v_0 \quad (8)$$

Plugging that into the previous equation, we get:

$$\left. \frac{dV_d}{dB} \right|_{\frac{\pi}{4}} = v_c L \left. \frac{dV_d}{d\theta} \right|_{\frac{\pi}{4}} = -v_0 v_c L \quad (9)$$

$$v_c = -\frac{\left. \frac{dV_d}{dB} \right|_{\frac{\pi}{4}}}{v_0 L} \quad (10)$$

All that is needed is $\left. \frac{dV_d}{dB} \right|_{\frac{\pi}{4}}$, which can be found by plotting the photodiode voltage at a relative polarizer angle of 45 degrees against corresponding magnetic field strengths. The error in voltage was calculated by applying our error in angle to the best fit trend lines centered at a relative polarizer angle of 45 degrees. From this, we can find the maximum and minimum possible slopes that would fit the set of points for $\left. \frac{dV_d}{dB} \right|_{\frac{\pi}{4}}$, and use the differences as error in our slope. Because the slope should be at a maximum value at 45 degrees, then at either point above or below that point, the slope will be lower than at 45 degrees. Since this means that any error will result in a lower than expected value, we will only consider the +error. The final result from this method was $v_c = 18.67 + 0.504 \frac{\text{rad}}{\text{m*T}}$.

IV. CONCLUSION

The errors in our final values were fairly good: about 2 percent on the direct method and about 3 percent for the slope method. Unfortunately, this means that the two results are inconsistent, as the minimum value for the direct method is $20.15 \frac{\text{rad}}{\text{m*T}}$ whereas the maximum value of the slope method is $19.17 \frac{\text{rad}}{\text{m*T}}$. While somewhat close, they still are distinctly different. These values are also different from the accepted $23 \frac{\text{rad}}{\text{m*T}}$ - being within 10 and 20 percent respectively. When looking at this experiment again, it could be useful to see if there are any changes in Verdet constant for the specific glass used in the rod compared with the general literature for glass, perhaps improving our accuracy. For reducing error even further, a combination of taking more data points and using a device - such as a computer controlled rotator - to be more precise in locking in to the correct angle would help a lot. And while our numbers were lower than expected instead of higher - indicating that zeroing and using the lock-in amplifier were fairly successful in removing contributions from room




FIG. 5. Change in the measured phase shift angle with the application of a magnetic field. The slope of the best fit is used in the direct measurement method of finding the Verdet constant.

light - having a way to box in the experiment set-up, thus blocking ambient light, would certainly be beneficial.