



Outside



Inside

Layers – From Outside to Inside

	mm
L1 Clear	5
L2 Clear PVB	1.52
L3 Clear	5



Interior Angle

Pane 5 mm Clear + 1.52 mm Clear PVB+ 5 mm Clear

Daylight Properties (EN 410)

Solar Energy Properties (EN 410)

Daylight Transmittance	: 88%
Daylight Reflectance Outdoor	: 8%
Daylight Reflectance Indoor	: 8%
Color Rendering Index (Ra)	: 98

Total Solar Energy Transmittance Solar Factor / g	: 76%
Solar Energy Direct Transmittance	: 70%
Solar Energy Reflectance Outdoor	: 7%
Solar Energy Absorption	: 23%
Shading Coefficient	: 0.87
UV Transmission	: 0%

Thermal Conductivity (EN 673)

U Value W/(m²K) : 5.3

Sound Insulation Values

Rw (C, Ctr) : 35 dB (-1, -3)

"Daylight" and "Solar Energy" properties are calculated using spectral measurements in compliance with EN 410:2011. "U-value" is calculated according to EN 673:2011. The emissivity measurements used for calculations comply with EN 673:2011 (Annex A) and EN 12898:2019. Thermal stresses or building codes may require the use of heat-treated glass. This document is not an evaluation of the risk of glass breakage from thermal stresses.

Data on acoustic parameters such as "Weighted Reduction (Rw)" and "Spectrum Adaption Terms C / Ctr" are specified based on estimations determined as the best result for this glazing composition and have not been tested. Performance on-site can be different, related to the sizes of the glazing, frame design, noise sources, etc. This document is only for informational purposes. Please contact your sales representative about whether the products you use in the calculation are available in our stock, whether they can be selling to your region, and the production time."