

Notes:

1. Appearance: smooth and flat, remove burrs, sharp edges, nodeformation;


2.The color of the surface powder is consistent with the drawing requirements or samples and color plates;

3. Before spraying, it must be pickled and phosphated, without hanging drops, stripes, blistering,orange peel, peeling, scratches and other defects;

4. The adhesion performance is reliable, and the marking test is not more than 1 grade. In general, coating The thickness is between 39~120um;

5. Meet ROHS standard

6.Surface finish: Black powder spraying

APPROVALS		DATE		ELEGOO 深圳市智能派科技有限公司 Shenzhen Elegoo Technology Co.,Ltd			
DRAWN							
CHECKED							
ISSUED							
		PART NAME		MATERIAL			
		Bottom Slider Plate		SPCC t=3			
General Tolerance Reference GB/T 1804-m		DRAWING NO.		SIZE	SCALE	REV.	
		Neptune 3-BJ-004		A4	1:2	A	
				UNIT: MM		SHEET 1 OF 1	