



RMN 3.2/

REV.	DATE	REVISION ORIGINOR	SIGN	ISSUED
(A)				
(B)				

- Notes:
1. Appearance: smooth and flat, remove burrs, sharp edges, nodeformation;
  2. The color of the surface powder is consistent with the drawing requirements or samples and color plates;
  3. Before spraying, it must be pickled and phosphated, without hanging drops, stripes, blistering, orange peel, peeling, scratches and other defects;
  4. The adhesion performance is reliable, and the marking test is not more than 1 grade. In general, coating The thickness is between 39~120um;
  5. Meet ROHS standard
  6. Surface finish: Black powder spraying

APPROVALS		DATE		ELEGOO 深圳市智能派科技有限公司 Shenzhen Elegoo Technology Co.,Ltd	
DRAWN				PART NAME Driven Plate_Z-axis	
CHECKED				MATERIAL SPCC t=2.5	
ISSUED				DRAWING NO. Neptune 3-BJ-002	
General Tolerance Reference GB/T 1804-m		SIZE A4		SCALE 1:1	REV. A
		UNIT: MM		SHEET 1 OF 1	