

# Test Report 測試報告

Number TWNC00978120

報告號碼

報告發行日期

Walsin Technology Corporation Issue Date Apr 29, 2021

申請廠商 華新科技股份有限公司 No. 566-1, Kaoshi Rd.,

Yangmei Dist., Taoyuan City 326,

Taiwan (R.O.C.)

桃園市楊梅區高獅路 566 之 1 號

Sample Description 樣品敘述:

One (1) Group of Submitted Samples Said To Be:

以下測試樣品乃供應商所提供及確認:

Sample Description : Multilayer Ceramic Capacitors

樣品名稱

Applicant:

Style / Item No. : NPO / X8G

產品型號

Date Sample Received : Apr 21, 2021

收件日期

**Date Test Started** : Apr 21, 2021

開始測試日期

Test Conducted 測試執行:

As requested by the applicant, for details please refer to attached pages.

依申請商之要求,細節請參考附頁.

Tested Components 測試元件:

(1) Mixed all kinds of submitted samples

(2) Brown electronic component (mixed all parts)(see photo)

Authorized By:

On behalf of Intertek Testing Services

Taiwan Limited

Matt Wang Director

Signed by:

Thomas Chou Manager

Page 1 of 15





: TWNC00978120

Test Conducted 測試內容:

Test Result Summary 測試結里:

Test Result Summary 測試結果:	T			I
<u>Test Item</u>	<u>Unit</u>	<u>Test Method</u>	Result 結果	RL
測試項目	單位	測試方法	<u>(1)(#)</u>	
Heavy Metal <u>重金屬</u>	_			
Cadmium (Cd) Content 鎘含量	ppm	With reference to IEC 62321-5: 2013, by microwave or acid digestion and determined by ICP-OES. 参考 IEC 62321-5: 2013,以微波或酸液消化法消化樣品並用感應耦合電漿原子發射光譜儀分析。	ND	2
Lead (Pb) Content 鉛含量	ppm	With reference to IEC 62321-5: 2013, by microwave or acid digestion and determined by ICP-OES. 参考 IEC 62321-5: 2013,以微波或酸液消化法消化樣品並用感應耦合電漿原子發射光譜儀分析。	ND	2
Mercury (Hg) Content 汞含量	ppm	With reference to IEC 62321-4:2013+AMD1:2017, by microwave or acid digestion and determined by ICP-OES. 参考 IEC 62321-4:2013+AMD1:2017,以微波或酸液消化法消化樣品並用感應耦合電漿原子發射光譜儀分析。	ND	2
Beryllium (Be) Content 鈹含量	ppm	With reference to USEPA 3052, by microwave digestion and determined by ICP-OES. 参考 USEPA 3052,以微波消化法並用感應耦合電漿原子發射光譜儀分析。	ND	2
Antimony (Sb) Content 銻含量	ppm	With reference to USEPA 3052, by microwave digestion and determined by ICP-OES. 参考 USEPA 3052,以微波消化法並用感應耦合電漿原子發射光譜儀分析。	ND	2
Chromium VI (Cr(VI)) Content 六價鉻含量	ppm	With reference to IEC 62321-7-2: 2017, organic solvent was used to dissolve or swell sample matrix, followed by alkaline digestion and determined by UV-Vis Spectrophotometer. 参考 IEC 62321-7-2:2017,以有機溶劑溶解或使樣品基質膨脹,再進行鹼液消化,用紫外光-可見光分光光度計分析。	ND	8









: TWNC00978120

Test Conducted 測試內容:

<u>Test Item</u>	<u>Unit</u>	<u>Test Method</u>	Result 結果	DI.
測試項目	單位	<u>測試方法</u>	(1)(#)	- <u>RL</u>
Polybrominated Biphenyls (PBE	s) 多溴聯	苯		1
Monobrominated Biphenyls (MonoBB) 單溴聯苯	ppm	With reference to IEC 62321-6: 2015, by solvent extraction and determined by GC-MS and further HPLC-DAD confirmation when necessary. 参考 IEC 62321-6: 2015,以溶劑萃取並用氣相層析質譜儀分析,必要時會以高效液相層析儀光二極體陣列偵測儀進行確認。	ND	5
Dibrominated Biphenyls (DiBB) 二溴聯苯	ppm		ND	5
Tribrominated Biphenyls (TriBB) 三溴聯苯	ppm		ND	5
Tetrabrominated Biphenyls (TetraBB) 四溴聯苯	ppm		ND	5
Pentabrominated Biphenyls (PentaBB) 五溴聯苯	ppm		ND	5
Hexabrominated Biphenyls (HexaBB) 六溴聯苯	ppm		ND	5
Heptabrominated Biphenyls (HeptaBB) 七溴聯苯	ppm		ND	5
Octabrominated Biphenyls (OctaBB) 八溴聯苯	ppm		ND	5
Nonabrominated Biphenyls (NonaBB) 九溴聯苯	ppm		ND	5
Decabrominated Biphenyl (DecaBB) 十溴聯苯	ppm		ND	5
Polybrominated Diphenyl Ether	s (PBDE	5) 多溴聯苯醚		
Monobrominated Diphenyl Ethers (MonoBDE) 單溴聯苯醚	ppm	With reference to IEC 62321-6: 2015, by solvent extraction and determined by GC-MS and further HPLC-DAD confirmation when necessary. 参考 IEC 62321-6: 2015,以溶劑萃取並用氣相層析質譜儀分析,必要時會以高效液相層析儀光二極體陣列偵測儀進行確認。	ND	5
Dibrominated Diphenyl Ethers (DiBDE) 二溴聯苯醚	ppm		ND	5
Tribrominated Diphenyl Ethers (TriBDE) 三溴聯苯醚	ppm		ND	5
Tetrabrominated Diphenyl Ethers (TetraBDE) 四溴聯苯醚	ppm		ND	5
Pentabrominated Diphenyl Ethers (PentaBDE) 五溴聯苯醚	ppm		ND	5
Hexabrominated Diphenyl Ethers (HexaBDE) 六溴聯苯醚	ppm		ND	5
Heptabrominated Diphenyl Ethers (HeptaBDE) 七溴聯苯醚	ppm		ND	5
Octabrominated Diphenyl Ethers (OctaBDE) 八溴聯苯醚	ppm		ND	5
Nonabrominated Diphenyl Ethers (NonaBDE) 九溴聯苯醚	ppm		ND	5
Decabrominated Diphenyl Ether (DecaBDE) 十溴聯苯醚	ppm		ND	5







Test Conducted 測試內容:

Number 報告號碼 : TWNC00978120

<u>Test Item</u>	<u>Unit</u>	<u>Test Method</u>	Result 結果	RL
測試項目	單位	測試方法	<u>(1)(#)</u>	<u>NL</u>
Phthalates 鄰苯二甲酸酯				
Di(2-ethylhexyl) Phthalate (DEHP) 鄰苯二甲酸二(2-乙基己基)酯	ppm		ND	50
Dibutyl Phthalate (DBP) 鄰苯二甲酸二丁酯	ppm		ND	50
Benzyl Butyl Phthalate (BBP) 鄰苯二甲酸苯基丁酯	ppm	With reference to IEC 62321-8:2017, by solvent extraction and determined by GC-MS. 参考 IEC 62321-8:2017,以溶 劑萃取並用氣相層析質譜儀分析。	ND	50
Di-(Iso-Nonyl) Phthalate (DINP) 鄰苯二甲酸二異壬酯	ppm		ND	50
Di-(Iso-Decyl) Phthalate (DIDP) 鄰苯二甲酸二異癸酯	ppm		ND	50
Di-(N-Octyl) Phthalate (DNOP) 鄰苯二甲酸二辛酯	ppm		ND	50
Diisobutyl Phthalate (DIBP) 鄰苯二甲酸二異丁酯	ppm		ND	50
Di-n-hexyl Phthalate (DNHP) 鄰苯二甲酸二正己酯	ppm		ND	50
Diheptyl Phthalate (DHP) 鄰苯二甲基二庚酯	ppm		ND	50
Di-n-pentyl Phthalate (DPP, DnPP,DPENP) 鄰苯二甲酸二戊酯	ppm		ND	50
Halogen Content 鹵素含量				
Fluorine (F) 氟	ppm	With reference to EN 14582:2016 by combustion	ND	50
Chlorine (CI) 氯	ppm	bomb with oxygen and determined by Ion	ND	50
Bromine (Br) 溴	ppm	Chromatography. 参考 EN 14582:2016,以氧彈	ND	50
Iodine (I) 碘	ppm	燃燒集氣法並用離子層析儀分 析。	ND	50







: TWNC00978120

Test Conducted 測試內容:

<u>Test Item</u>	<u>Unit</u>	Test Method	Result 結果	. RL
測試項目	單位	測試方法	(1)(#)	<u>KL</u>
Others 其他				
Hexabromocyclododecane (HBCDD) 六溴環十二烷	ppm	With reference to USEPA 3540C, by solvent extraction and determined by GC-MS. 参考 USEPA 3540C,以溶劑萃 取並用氣相層析質譜儀分析。	ND	10
Perfluorooctane Sulfonates Including PFOS, PFOSA, N-Me-FOSA, N-Et-FOSA, N-Me-FOSE, N-Et-FOSE 全氟辛磺酸含 PFOS, PFOSA, N-Me-FOSA, N-Et-FOSA, N-Me-FOSE, N-Et-FOSE	ppm	With reference to CEN/TS 15968:2010, by solvent extraction and determined by LC-MS-MS. 参考 CEN/TS 15968:2010,以 溶劑萃取並用液相層析串聯質 譜儀分析。	ND	0.01
Perfluorooctanoic Acid (PFOA) 全氟辛酸	ppm	With reference to CEN/TS 15968:2010, by solvent extraction and determined by LC-MS-MS. 参考 CEN/TS 15968:2010,以 溶劑萃取並用液相層析串聯質 譜儀分析。	ND	0.01

Test Item	<u>Unit</u>	Test Method	Result 結果	RL
測試項目	<u>單位</u>	<u>測試方法</u>	<u>(2)</u>	<u>1XL</u>
Red Phosphorus 紅磷	NA	Analysis was performed by Pyrolyzer-GS/MS. 以熱裂解儀-氣相層析質譜儀分析。	Negative	NA

Remarks: ppm = Parts per million based on weight of tested sample = mg/kg

備註

百萬分之一,依據測試樣品重量計算 = 毫克/公斤

ND = Not detected 未檢測出

RL = Reporting limit, quantitation limit of analyte in sample

報告極限,測試樣品之定量偵測極限

NA = Not applicable 不適用

# = Test results were for reference only and might not represent the real content in each component as the composite sampling procedure was according to the special request of client. Please be noted the fewer components are mixed up, the better representation of sampling will get.

依據客戶要求進行混合測試,故本測試結果僅供參考,且該混測結果不一定能代表各分測結果。請

注意混測數量越少,各樣品取樣代表性會越佳。

Responsibility of Chemist 分析人員 : Melody Lee/ Vita Fu

Date Sample Received 樣品收件日期 : Apr 21, 2021

Test Period 樣品測試期間 : Apr 21, 2021 to Apr 29, 2021







: TWNC00978120

Test Conducted 測試內容:

#### RoHS Limit RoHS 限值

Restricted Substances 限用物質	<u>Limits 限值</u>
Cadmium (Cd) content 鎘含量	0.01% (100ppm)
Lead (Pb) content 鉛含量	0.1% (1000ppm)
Mercury (Hg) content 汞含量	0.1% (1000ppm)
Chromium VI ((Cr(VI)) content 六價鉻含量	0.1% (1000ppm)
Polybrominated Biphenyls (PBBs) 多溴聯苯	0.1% (1000ppm)
Polybrominated Diphenyl Ethers (PBDEs) 多溴聯苯醚	0.1% (1000ppm)
Di(2-ethylhexyl) Phthalate (DEHP) 鄰苯二甲酸二(2-乙基己基)酯	0.1% (1000ppm)
Dibutyl Phthalate (DBP) 鄰苯二甲酸二丁酯	0.1% (1000ppm)
Benzyl Butyl Phthalate (BBP) 鄰苯二甲酸苯基丁酯	0.1% (1000ppm)
Diisobutyl Phthalate (DIBP) 鄰苯二甲酸二異丁酯	0.1% (1000ppm)

The limits were quoted from Annex II of 2011/65/EU and Amendment (EU) 2015/863 for homogeneous material. 本限值是依據歐盟指令 2011/65/EU 及其更新指令(EU) 2015/863 之附錄二針對均質材質所訂定。







: TWNC00978120


Test Conducted 測試內容:

#### Measurement Flowchart 測試流程圖:

Test for Cd/Pb/Hg/Chromium (VI)/PBBs/PBDEs Content RoHS 六項測試

Reference Method 參考方法: Cd/Pb: IEC 62321-5:2013; Hg: IEC 62321-4:2013+AMD1:2017;

Chromium (VI): IEC 62321-7-1:2015 (boiling water extraction); Chromium (VI): IEC 62321-7-2:2017 (solvent and alkaline extraction); PBBs/PBDEs: IEC 62321-6:2015









Number

: TWNC00978120

報告號碼

### Test Conducted 測試內容:

# Remark 備註:

\*1: List of Appropriate Acid 各材質添加酸液如下表:

The springer of the control of the springer of			
Material 材質	Acid Added for Digestion 添加酸液種類		
Polymers 聚合物	HNO <sub>3,</sub> HCl,HF,H <sub>2</sub> O <sub>2,</sub> H <sub>3</sub> BO <sub>3</sub> 硝酸、鹽酸、氫氟酸、雙氧水、硼酸		
Metals 金屬	HNO <sub>3,</sub> HCl,HF 硝酸、鹽酸、氫氟酸		
Electronics 電子產品	HNO <sub>3,</sub> HCl,H <sub>2</sub> O <sub>2,</sub> HBF <sub>4</sub> 硝酸、鹽酸、雙氧水、氟硼酸		

\*2: If sample solution is significantly more intense than 0.13 µg/cm² equivalent comparison standard, Chromium VI would be determined as detected, the result of visual observation is positive.

當待測樣品溶液顏色明顯比 0.13 μg/cm² 深,採用目測法判定六價鉻結果爲陽性。








: TWNC00978120

Test Conducted 測試內容:

Measurement Flowchart 測試流程圖:

Test for Heavy Metal (Be,Sb) Content 重金屬(鈹,銻)

Reference Method 參考方法: USEPA 3052










: TWNC00978120

Test Conducted 測試內容:

Measurement Flowchart 測試流程圖:

Test for Phthalates Content 鄰苯二甲酸酯測試 Reference Method 參考方法: IEC 62321-8:2017










: TWNC00978120

Test Conducted 測試內容:

Measurement Flowchart 測試流程圖:

Test for Halogen Content 鹵素測試

Reference Method 參考方法: EN 14582:2016










: TWNC00978120

Test Conducted 測試內容:

Measurement Flowchart 測試流程圖:

Test for Hexabromocyclododecane (HBCDD) 六溴環十二烷測試 Reference Method 參考方法: USEPA 3540C










: TWNC00978120

Test Conducted 測試內容:

Measurement Flowchart 測試流程圖:

Test for Perfluorooctane Sulfonates (PFOS) / Perfluorooctanoic Acid (PFOA) Content 全氟辛磺酸 /全氟辛酸測試 Reference Method 參考方法: CEN/TS 15968:2010










: TWNC00978120

Test Conducted 測試內容:

Measurement Flowchart 測試流程圖:

Test for Red Phosphorus Content 紅磷測試

Reference Method 參考方法: Pyrolyzer-GS/MS analysis









: TWNC00978120


# Sample photo 樣品照片:

(1)

(2)









End of Report

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: <a href="http://www.intertek-twn.com/terms/">http://www.intertek-twn.com/terms/</a> . Intertek's responsibility and liability are limited to the terms and conditions of the agreement.

This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.

Reporting Statements of Conformity: Please note that the test results contain statement of conformity with the decision rules which are based on the specifications of customers, regulations and standards, and does not consider measurement uncertainty.



