

1. Discuss why space charge limited conduction could occur in a device comprised of an a-semiconductor. Use energy band diagrams in your discussion.
-
2. The UV-Vis transmission data is shown for several a-semiconductor films in **Fig. 1**. Based on the optical data, what can you say about the effect of the particular dopant on the sample? Which sample would you expect to have the most defects? Describe why you support your conclusions.




Figure 1: UV-Vis % transmission data for $\text{Ge}_{40}\text{Se}_{60}$ films.

The approximate optical bandgap is shown by taking the tangent of the linear portions of the optical data and finding the intercept at 0% transmission. The original $\text{Ge}_{40}\text{Se}_{60}$ sample and those doped with A, C, and D give optical bandgaps around 300 nm or ≈ 4 eV ($\lambda = hc/E$), while $\text{Ge}_{40}\text{Se}_{60} + \text{B}$ has an optical bandgap of approximately 250 nm or ≈ 5 eV. While electrical conduction ideally requires transitions from the valence extended states to the conduction extended states, the optical band gap can include shorter transitions from the localized states in the gap to the conduction extended states. As seen in Raty et al.'s study of aging in phase change materials [1], a decrease in localized defect states leads to band gap widening. Of the four dopant samples, $\text{Ge}_{40}\text{Se}_{60} + \text{D}$ leads to the smallest optical band gap (≈ 4 eV) and thus likely has the most defects.

3. Compare and contrast the derivation of the density of states for a crystalline semiconductor with that of an amorphous semiconductor.

-
4. Describe conduction in the extended states, band tail (mobility edge) states, and in the gap states.
-

5. Suppose you are going to make electrical measurements on an a-semiconductor. How would you do this to ensure you could differentiate between contributions to current due to extended states conduction, tunneling, and variable range hopping? Describe each of these conduction mechanisms in your answer.

References

- [1] J. Y. Raty, W. Zhang, J. Luckas, C. Chen, R. Mazzarello, C. Bichara, M. Wuttig, Aging mechanisms in amorphous phase-change materials, *Nature Communications* 6 (7467) (2015) 1–8. doi:10.1038/ncomms8467.
URL <http://dx.doi.org/10.1038/ncomms8467>