

RESERVE FACTORS SUMMARY											
STRUCTURAL COMPONENT:						REFERENCE DOCUMENT:					
ZONE	ELEMENT	DRAWING	MATERIAL & TEMPER	LOAD CASE	LOAD TYPE	M A G	APPLIED VALUE	ALLOWABLE VALUE	R.F.	REFERENCE PAGE	
				TEMPERAT.						REMARKS	
Wing Upper Skin	Stringer No. 13 bt'n ribs 33 - 34		7075;T76511 7075;T76	1	C	F	-141675.	-66866.	0.47	Failure type: Local buckling	
					S	Q	183.6	86.6			
					S	Q	139.7	66.0			
Wing Lower Skin	Stringer No. 17 bt'n ribs 33 - 34		2024;T42 2024;T3	2	C	F	-99970.	-67829.	0.68	Failure type: Post-buckling Column buckling	
					S	Q	-10.3	-7.0			
					S	Q	-61.4	-41.7			
LOAD TYPES:				MAGNITUDES:				RESERVE FACTOR:			
T: TENSION S: SHEAR BD: BENDING P: PRESSURE				C: COMPRESSION TO: TORSION TBR: BEARING				RF = $\frac{\text{ALLOWABLE VALUE}}{\text{APPLIED VALUE}}$			