

Certificate 3.1

 Test Report
 24035580
 Page
 1

 Test Date
 03/09/24
 Page
 1

RGPBALLS S.R.L.

Via E. De Amicis 59/C - 61/A 20092 Cinisello Balsamo (MI) - Italy VAT N° e C.F. 08678490965

Num. Rea MI-2042305 Cap. Soc. 1.000.000 € I.V.

Tel. +39 02.617.88.57 - +39 02.66.01.70.32

Email: rgpballs@rgpballs.com

www.rgpballs.com

Customer

ROLLER INDUSTRIAL S.A.

P.I. LEZAMA-LEGUIZAMON C/ZUBEROA 1, 2°DCHA

ETXEBARRI (VIZCAYA) 48450

ES

N° RGP Order Delivery Number	24024198 O2 1,00 24201508	Shipment Date 08/08/24 Quantity 30000,00 NR	Ref.Custome	202.400.996	
Item Item Description Lot Number Production Date	SF52100085000 - 031640 BALLS 52100 MM.8,5000 3043085005 30/04/23	Heat Nu Grade HRC Sorting	mber	D12208097XX G 100 60-66 +/-0 µm	ISO 3290-1:2014 ANSI/ABMA/ISO 3290-1:2014 DIN 5401:2002
CHEMICAL COMPOSITION		Sorting		+7-0 μm	

CHEMICAL COM	PUSITION	
683-17.2014	100Cr6/1	3505

GCr15 steel equivalent to US AISI SAE ASTM A295, European EN, Germany DIN, Japanese JIS, British BSI, France NF and ISO standard.

Chemical Composition Minimum Value Maximum Value Result Value

COMPILED BY:

CHECKED BY:

QA MANAGER :

Massimiliano Ferro

Niki Scavullo

Andrea Rossi



Certificate 3.1
UNI EN 10204:2005

Test Report 24035580 **Test Date** 03/09/24 Page

2

RGPBALLS S.R.L.

Via E. De Amicis 59/C - 61/A 20092 Cinisello Balsamo (MI) - Italy VAT N° e C.F. 08678490965 Num. Rea MI-2042305

Cap. Soc. 1.000.000 € I.V.

Tel. +39 02.617.88.57 - +39 02.66.01.70.32

Email: rgpballs@rgpballs.com

www.rgpballs.com

Customer

ROLLER INDUSTRIAL S.A.

P.I. LEZAMA-LEGUIZAMON C/ZUBEROA 1, 2°DCHA

ETXEBARRI (VIZCAYA) 48450

ES

N° RGP Order Delivery Number	24024198 O2 1,00 24201508	Shipment Date 08/08/24 Quantity 30000,00 NR	Ref.Custome	202.400.996		
Item Item Description Lot Number Production Date	SF52100085000 - 031640 BALLS 52100 MM.8,5000 3043085005 30/04/23	Heat Nun Grade HRC Sorting	nber	D12208097XX G 100 60-66 +/-0 μm	ISO 3290-1:2014 ANSI/ABMA/ISO 3290-1:2014 DIN 5401:2002	

MECHANICAL TESTS

	DIAMETER VARIATION UNI EN ISO $17450-2:2012$ Min Max $-2,5$ μ m $+2,5$ μ m	ROUNDNESS UNI EN ISO 12181-2:2011 Min Max 0,0 μm 2,5 μm	ROUGHNESS -Ra UNI EN ISO 1302:2002 Min Max 0,0 μ m 0,10 μ m	HARDNESS UNI EN ISO 6508-1:2015 UNI EN ISO 6507-1:2005 Min Max 60,0 66,0 HRC
Sample N°	Result Value	Result Value	Result Value	Result Value
1	-0,200	0,610	0,020	65,0
2	0,500	0,500	0,020	64,5
3	0,100	0,550	0,020	64,5
4	-0,400	0,620	0,020	65,0
5	0,200	0,580	0,020	64,5
6	-0,500	0,520	0,020	65,0
7	-0,300	0,530	0,020	64,5
8	0,100	0,600	0,020	64,5
9	-0,300	0,550	0,020	65,0
10	0,200	0,520	0,020	65,0

COMPILED BY:

CHECKED BY:

QA MANAGER :

Massimiliano Fe rio

NikiScavullo

Andrea Rossi