

CLH2 is transparent BOPP film, both sides are treated and both sides are heat sealable. The film has good mechanical, antistatic and slip properties.

APPLICATIONS

- Lamination
- HFFS and VFFS packaging
- General Wrapping



Properties	Typical Values		Method	Unit
Nominal Thickness	20	30	ITM	µm
Unit Weight	18,2	27,3	ITM	g/m ²
Average Yield	54,9	36,6	ITM	m ² /kg
Gloss (45°)	≥85		ASTM D 2457	Gloss unit
Haze	<2,5	<3,5	ASTM D 1003	%
Treatment Level			ASTM D 2578	dynes/cm
	Print Side	≥38		
	Back Side	≥36		
Tensile Strength			ASTM D 882	N/mm ²
	MD	140		
	TD	280		
Elongation at Break			ASTM D 882	%
	MD	180		
	TD	50		
Coefficient of Friction			ASTM D1894	
<i>dynamic</i>	B/B	≤0,30		
	B/M	≤0,25		
Heat Seal Temperature	110 - 145			3 bar- 0,5 sec
Seal Strength	>2,2	>2,8		130 C /3 bar/ 0,5 sec
Thermal Shrinkage			ITM	130 °C 7 MIN
	MD	≤5,0		
	TD	≤3,0		

MD: Machine direction
TD: Transverse direction
B: Back
M: Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

CLH2 complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com