

CLR is transparent release BOPP film, non heat sealable, one side is treated. The film has low haze, high gloss, good release properties and excellent stiffness properties.

APPLICATIONS

- Release film for cold seal applications



Properties	Typical Values	Method	Unit
Nominal Thickness	15 20	ITM	μm
Unit Weight	13,7 18,2	ITM	g/m ²
Average Yield	73,3 54,9	ITM	m ² /kg
Gloss (45°)	≥90	ASTM D 2457	Gloss unit
Haze	<2,0	ASTM D 1003	%
Treatment Level	≥38	ASTM D 2578	dynes/cm
Tensile Strength			
	MD 120	ASTM D 882	N/mm ²
	TD 270		
Elongation at Break			
	MD 180	ASTM D 882	%
	TD 50		
Coefficient of Friction			
<i>dynamic</i>	B/B ≤0,40	ASTM D1894	
	B/M ≤0,30		
Thermal Shrinkage			
	MD ≤5,0	ITM	130 °C 7 MIN
	TD ≤3,0		

MD: Machine direction
TD: Transverse direction
B: Back
M: Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

CLR complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com