

OMI is a white voided OPP film, matt on both sides. Its special formulation results in a film with very high yield. The film is treated on both sides. The roll wound print side outside.



APPLICATIONS

- Improved sheet fed performance
- Outstanding opacity and whiteness
- Good antistatic properties, web flatness, machineability and die cutting
- High yield and soft touch effect after moulding
- UV curing and oxidative drying inks.
- Suitable for gravure and UV-flexo printing
- For reel to reel printing with UV inks, inline Corona treatment is strongly recommended

Properties	OMI50	OMI60	Method	Unit
Nominal Thickness	50	60	ISO 4591	μm
Unit Weight	27,5	33	ISO 4591	g/m ²
Average Yield	36,4	30,3	ISO 4591	m ² /kg
Opacity	86	88	DIN 53146	%
Gloss (45° Printsides)	20	20	ASTM D 2457	Gloss unit
Treatment Level	min. 38	min. 38	ASTM D 2578	dynes/cm
Tensile Strength				
MD	50	60	ASTM D 882	N/mm ²
TD	100	120		
Elongation at Break				
MD	120	120	ASTM D 882	%
TD	30	30		

MD: Machine direction
TD : Transverse direction
B : Back
M : Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

OMI complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com