

OPD is white opaque BOPP film, both sides heat sealable, one side is treated. The film has outstanding whiteness and opacity, high gloss and excellent stiffness properties.

APPLICATIONS

- General Purpose Packaging
- Both for Single Layer and Lamination



- Treated Sealable Layer
- OPP Layer
- White Voided OPP Core Layer
- OPP Layer
- Sealable Layer

Properties		Typical Values		Method	Unit
Nominal Thickness		30	35	ITM	μm
Unit Weight		22,2	25,9	ITM	g/m ²
Average Yield		45	38,6	ITM	m ² /kg
Gloss (45°)		≥90		ASTM D 2457	Gloss unit
Opacity		min 85		ASTM D 1003	%
Treatment Level		≥38		ASTM D 2578	dynes/cm
Tensile Strength				ASTM D 882	N/mm ²
	MD TD	90 180			
Elongation at Break				ASTM D 882	%
	MD TD	150 40			
Coefficient of Friction				ASTM D1894	
<i>dynamic</i>	B/B B/M	≤0,30 ≤0,25			
Thermal Shrinkage				ITM	130 °C 7 MIN
	MD TD	≤5,0 ≤3,0			

MD: Machine direction
TD : Transverse direction
B : Back
M : Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

OPD complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com