

OPH is white opaque BOPP film, both sides heat sealable, one side is treated. The film has outstanding whiteness and opacity, high gloss and excellent stiffness properties.

APPLICATIONS

- General Purpose Packaging
- Both for Single Layer and Lamination



- Treated Sealable Layer
- OPP Layer
- White Voided OPP Core Layer
- OPP Layer
- Sealable Layer

Properties	Typical Values			Method	Unit
Nominal Thickness	30	35	40	ITM	μm
Unit Weight	21,0	24,5	28,0	ITM	g/m ²
Average Yield	47,6	40,8	35,7	ITM	m ² /kg
Gloss (45°)	≥90			ASTM D 2457	Gloss unit
Opacity	min 80			ASTM D 1003	%
Treatment Level	≥38			ASTM D 2578	dynes/cm
Tensile Strength				ASTM D 882	N/mm ²
	MD	90			
	TD	200			
Elongation at Break				ASTM D 882	%
	MD	180			
	TD	50			
Coefficient of Friction				ASTM D1894	
	B/B	≤0,35			
<i>dynamic</i>	B/M	≤0,25			
Heat Seal Temperature	110 - 145				3 bar- 0,5 sec
Seal Strength	>2,0				130 C /3 bar/ 0,5 sec
Thermal Shrinkage				ITM	130 °C 7 MIN
	MD	≤5,0			
	TD	≤3,0			

MD: Machine direction
TD : Transverse direction
B : Back
M : Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

OPH complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com