

OPL is white opaque BOPP film, both sides treated. The film has outstanding whiteness and opacity, high gloss and excellent stiffness properties.

APPLICATIONS

- White opaque film for surface printing
- Cold Seal and Release Lacquer applications
- Lamination applications



Properties		Typical Values				Method	Unit
Nominal Thickness		30	35	40	50	ITM	µm
Unit Weight		21,0	24,5	28,0	35,0	ITM	g/m²
Average Yield		47,6	40,8	35,7	28,5	ITM	m²/kg
Gloss (45°)		≥90				ASTM D 2457	Gloss unit
Opacity		min 80				ASTM D 1003	%
Treatment Level		≥38				ASTM D 2578	dynes/cm
Tensile Strength						ASTM D 882	N/mm²
	MD	90					
	TD	200					
Elongation at Break						ASTM D 882	%
	MD	180					
	TD	50					
Coefficient of Friction						ASTM D1894	
	B/B	≤0,45					
	B/M	≤0,30					
Thermal Shrinkage						ITM	130 °C 7 MIN
	MD	≤5,0					
	TD	≤3,0					

MD: Machine direction
TD: Transverse direction
B: Back
M: Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

OPL complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com