

OPS is a white opaque BOPP film, one-side treated. The film has outstanding whiteness, high opacity and excellent stiffness properties. It contains no migratory additives and is suitable with most adhesive systems; provides excellent converting, die-cutting and label dispensing performance.

APPLICATIONS

- High stiff BOPP film for self-adhesive label
- Compatible with most label printing technologies.



Properties	Typical Values	Method	Unit
Nominal Thickness	57	ITM	μm
Unit Weight	41	ITM	g/m ²
Average Yield	24,4	ITM	m ² /kg
Gloss (45°)	≥60	ASTM D 2457	Gloss unit
Opacity	min 90	ASTM D 1003	%
Treatment Level	≥38	ASTM D 2578	dynes/cm
Tensile Strength		ASTM D 882	N/mm ²
	MD 90 TD 180		
Elongation at Break		ASTM D 882	%
	MD 150 TD 25		
Thermal Shrinkage		ITM	130 °C 7 MIN
	MD ≤4 TD ≤2		

MD: Machine direction
TD: Transverse direction
B: Back
M: Metal

The data and figures provided in datasheet are intended to provide general information about our products. They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

OPS complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com