

OWR is white opaque BOPP film, one side is treated. The film has outstanding whiteness and opacity, high gloss and excellent stiffness properties.

APPLICATIONS

- White opaque film for surface printing
- Designed specially for reel fed label applications



- Treated Layer
- Inner OPP Layer
- White Voided OPP Core Layer
- Inner OPP Layer
- Non Treated Layer

Properties	Typical Values		Method	Unit
Nominal Thickness	35	38	ITM	μm
Unit Weight	24,5	26,6	ITM	g/m ²
Average Yield	40,8	37,6	ITM	m ² /kg
Gloss (45°)	≥90		ASTM D 2457	Gloss unit
Opacity %	min 80		ASTM D 1003	%
Treatment Level	≥38		ASTM D 2578	dynes/cm
Tensile Strength			ASTM D 882	N/mm ²
MD	100			
TD	200			
Elongation at Break			ASTM D 882	%
MD	130			
TD	45			
Coefficient of Friction			ASTM D1894	
B/B	≤0,35			
B/M	≤0,25			
Thermal Shrinkage			ITM	130 °C 7 MIN
MD	≤5,0			
TD	≤3,0			

MD: Machine direction
TD : Transverse direction
B : Back
M : Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

OWR complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com