

OWRD is white opaque BOPP film, one side is treated. The film has outstanding whiteness and opacity, high gloss and excellent stiffness properties.

APPLICATIONS

- White opaque film for surface printing
- Designed specially for reel fed label applications



Properties		Typical Values	Method	Unit
Nominal Thickness		38	ITM	μm
Unit Weight		28,1	ITM	g/m²
Average Yield		35,6	ITM	m²/kg
Gloss (45°)		≥90	ASTM D 2457	Gloss unit
Opacity %		min 80	ASTM D 1003	%
Treatment Level		≥38	ASTM D 2578	dynes/cm
Tensile Strength	MD	100	ASTM D 882	N/mm²
	TD	200		
Elongation at Break	MD	130	ASTM D 882	%
	TD	45		
Coefficient of Friction	B/B	≤0,35	ASTM D1894	
<i>dynamic</i>	B/M	≤0,25		
Thermal Shrinkage	MD	≤5,0	ITM	130 °C 7 MIN
	TD	≤3,0		

MD: Machine direction
TD: Transverse direction
B: Back
M: Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

OWRD complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com