

OWRL is white opaque BOPP film, one side is treated. The film has outstanding whiteness and opacity, high gloss and excellent stiffness properties. The film use has improved yield properties.

APPLICATIONS

- White opaque film for surface printing
- Designed specially for reel fed label applications



Properties	Typical Values			Method	Unit
Nominal Thickness	35	38	47	ITM	μm
Unit Weight	21,7	23,6	29,2	ITM	g/m ²
Average Yield	46,1	42,4	34,2	ITM	m ² /kg
Opacity %	min 80			ASTM D 1003	%
Treatment Level	≥38			ASTM D 2578	dynes/cm
Tensile Strength	MD	90	150	ASTM D 882	N/mm ²
	TD	150			
Elongation at Break	MD	115	30	ASTM D 882	%
	TD	30			
Coefficient of Friction	B/B	≤0,35	≤0,25	ASTM D1894	
<i>dynamic</i>	B/M	≤0,25			
Thermal Shrinkage	MD	≤5,0	≤3,0	ITM	130 °C 7 MIN
	TD	≤3,0			

MD: Machine direction
TD: Transverse direction
B: Back
M: Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

OWRL complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com