

WLL is white BOPP film, both sides heat sealable, both sides treated. The film has high protection for light and excellent stiffness properties.

APPLICATIONS

- Food packaging



- Treated Sealable Layer
- OPP Layer
- White OPP Core Layer
- OPP Layer
- Treated Sealable Layer

Properties		Typical Values			Method	Unit
Nominal Thickness		20	25	30	ITM	μm
Unit Weight		18,8	23,5	28,2	ITM	g/m²
Average Yield		53,2	42,55	35,4	ITM	m²/kg
Gloss (45°)		≥55			ASTM D 2457	Gloss unit
Light Transmission		46	41	37	ASTM D 1003	%
Treatment Level		≥38			ASTM D 2578	dynes/cm
Tensile Strength					ASTM D 882	N/mm²
	MD	140				
	TD	280				
Elongation at Break					ASTM D 882	%
	MD	180				
	TD	50				
Coefficient of Friction					ASTM D1894	
	B/B	≤0,45				
	B/M	≤0,25				
Heat Seal Temperature		110 - 145				3 bar- 0,5 sec
Seal Strength		>2,8				130 C /3 bar/ 0,5 sec
Thermal Shrinkage					ITM	130 °C 7 MIN
	MD	≤5,0				
	TD	≤3,0				

MD: Machine direction
TD : Transverse direction
B : Back
M : Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

WLL complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com