

CLH1 is transparent BOPP film, both sides are sealable, one side is treated. The film has good mechanical, antistatic and slip properties.

APPLICATIONS

- Rotogravure and flexographic printing
- Lamination
- HFFS and VFFS packaging
- General Wrapping
- Good wire-sealability in bag-making processes



— Treated Sealable Layer
 — OPP Layer
 — OPP Core Layer
 — OPP Layer
 — Sealable Layer

Properties		Typical Values						Method	Unit	
Nominal Thickness		15	17	20	25	30	35	40	ITM	µm
Unit Weight		13,7	15,5	18,2	22,8	27,3	31,9	36,4	ITM	g/m²
Average Yield		73,3	64,6	54,9	44,0	36,6	31,4	27,5	ITM	m²/kg
Gloss (45°)		≥85						ASTM D 2457	Gloss unit	
Haze		<2,5			<3,5			ASTM D 1003	%	
Treatment Level		≥38						ASTM D 2578	dynes/cm	
Tensile Strength		MD TD140 280						ASTM D 882	N/mm²	
Elongation at Break		MD TD180 50						ASTM D 882	%	
Coefficient of Friction		B/B B/M≤0,30 ≤0,25						ASTM D1894		
<i>dynamic</i>										
Heat Seal Temperature		110 - 145						3 bar- 0,5 sec		
Seal Strength		>2,3			>3	>3,5			130 C /3 bar/ 0,5 sec	
Thermal Shrinkage		MD TD≤5,0 ≤3,0						ITM	130 °C 7 MIN	

MD: Machine direction
 TD : Transverse direction
 B : Back
 M : Metal

The data and figures provided in datasheet are intended to provide general information about our products .
 They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

CLH1 complies with EU and FDA regulations.

Polikon Plastik Film
 Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
 Phone: +90 232 880 40 34 35
 Fax: +90 232 880 40 33
 www.polikonfilm.com