

CLM is transparent BOPP film, both sides are sealable, one side is treated. The film has good mechanical, antistatic and slip properties.

APPLICATIONS

- General purpose packaging film with strong seal
- HFFS and VFFS packaging
- General Wrapping
- Good wire-sealability in bag-making processes



—— Treated Sealable Layer
 —— OPP Layer
 —— OPP Core Layer
 —— OPP Layer
 —— Sealable Layer

Properties	Typical Values		Method	Unit
Nominal Thickness	25	30	ITM	μm
Unit Weight	22,8	27,3	ITM	g/m ²
Average Yield	44,0	36,6	ITM	m ² /kg
Gloss (45°)	≥85		ASTM D 2457	Gloss unit
Haze	<2,5		ASTM D 1003	%
Treatment Level	≥38		ASTM D 2578	dynes/cm
Tensile Strength			ASTM D 882	N/mm ²
MD	140			
TD	280			
Elongation at Break			ASTM D 882	%
MD	180			
TD	50			
Coefficient of Friction			ASTM D1894	
dynamic	B/B	≤0,25		
	B/M	≤0,20		
Heat Seal Temperature	105 - 145			3 bar- 0,5 sec
Seal Strength	>3			130 C /3 bar/ 0,5 sec
Thermal Shrinkage			ITM	130 °C 7 MIN
MD	≤5,0			
TD	≤3,0			

MD: Machine direction
 TD : Transverse direction
 B : Back
 M : Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
 They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

CLM complies with EU and FDA regulations.

Polikon Plastik Film
 Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
 Phone: +90 232 880 40 34 35
 Fax: +90 232 880 40 33
 www.polikonfilm.com