

CMH is one side matte heat sealable BOPP film, gloss side is treated. The film has silky feel and excellent stiffness properties.

APPLICATIONS

- Snacks packaging
- Lamination
- Book Cover



Properties		Typical Values		Method	Unit	
Nominal Thickness		15	20	25	ITM	μm
Unit Weight		13,2	17,6	22	ITM	g/m²
Average Yield		75,8	56,8	45,5	ITM	m²/kg
Gloss (45°)		<11		ASTM D 2457	Gloss unit	
Haze		75		ASTM D 1003	%	
Treatment Level		≥38		ASTM D 2578	dynes/cm	
Tensile Strength				ASTM D 882	N/mm²	
	MD	120				
	TD	270				
Elongation at Break				ASTM D 882	%	
	MD	180				
	TD	50				
Coefficient of Friction				ASTM D1894		
	B/B	≤0,35				
	B/M	≤0,25				
Heat Seal Temperature		110 - 145			3 bar- 0,5 sec	
Seal Strength		>2,3			130 C /3 bar/ 0,5 sec	
Thermal Shrinkage				ITM	130 °C 7 MIN	
	MD	≤5,0				
	TD	≤3,0				

MD: Machine direction
TD : Transverse direction
B : Back
M : Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

CMH complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com