

CMI is a transparent OPP film, matt on one sides.
CMI is treated on both sides.



APPLICATIONS

- Improved sheet fed performance
- Good antistatic properties, web flatness, machineability and die cutting
- UV curing and oxidative drying inks.
- Suitable for gravure and UV-flexo printing
- For reel to reel printing with UV inks, inline corona treatment is strongly recommended

Properties	CMI50	CMI55	Method	Unit
Nominal Thickness	50	55	ISO 4591	μm
Unit Weight	44,5	49	ISO 4591	g/m ²
Average Yield	22,5	20,4	ISO 4591	m ² /kg
Gloss (45° Printsides)	50	50	ASTM D 2457	Gloss unit
Treatment Level	min. 38	min. 38	ASTM D 2578	dynes/cm
Tensile Strength				
	MD	120	ASTM D 882	N/mm ²
	TD	240		
Elongation at Break				
	MD	200	ASTM D 882	%
	TD	50		

MD: Machine direction
TD: Transverse direction
B: Back
M: Metal

*The data and figures provided in datasheet are intended to provide general information about our products.
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

CMI complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com