

CMP2 is transparent BOPP film, non heat sealable, both side is treated. The film has silky feel and paper look impression, printable on matt side.

APPLICATIONS

- Graphic Art
- Paper Lamination
- Lamination Film



— Treated Matte Layer
— OPP Layer
— OPP Core Layer
— OPP Layer
— Treated Plain Layer

Properties		Typical Values		Method	Unit
Nominal Thickness		12	15	ITM	μm
Unit Weight		10,6	13,2	ITM	g/m²
Average Yield		94,7	75,7	ITM	m²/kg
Gloss (45°)		<9		ASTM D 2457	Gloss unit
Haze		--		ASTM D 1003	%
Treatment Level		≥38		ASTM D 2578	dynes/cm
Tensile Strength	MD	140		ASTM D 882	N/mm²
	TD	280			
Elongation at Break	MD	180		ASTM D 882	%
	TD	50			
Coefficient of Friction	B/B	≤0,30		ASTM D1894	
<i>dynamic</i>	B/M	≤0,25			
Thermal Shrinkage	MD	≤5,0		ITM	130 °C 7 MIN
	TD	≤3,0			

MD: Machine direction
TD : Transverse direction
B : Back
M : Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

CMP2 complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com