

CMR is one side matte release surface, gloss side is treated.
The film has silky feel and excellent stiffness properties.

APPLICATIONS

- Release film for cold seal applications



- Treated Layer
- OPP Layer
- OPP Core Layer
- OPP Layer
- Release Matte Layer

Properties		Typical Values	Method	Unit
Nominal Thickness		20	ITM	μm
Unit Weight		17,6	ITM	g/m²
Average Yield		56,8	ITM	m²/kg
Gloss (45°)		<11	ASTM D 2457	Gloss unit
Haze		75	ASTM D 1003	%
Treatment Level		≥38	ASTM D 2578	dynes/cm
Tensile Strength	MD	120	ASTM D 882	N/mm²
	TD	270		
Elongation at Break	MD	180	ASTM D 882	%
	TD	50		
Coefficient of Friction <i>dynamic</i>	B/B	≤0,35	ASTM D1894	
	B/M	≤0,25		
Thermal Shrinkage	MD	≤5,0	ITM	130 °C 7 MIN
	TD	≤3,0		

MD: Machine direction
TD : Transverse direction
B : Back
M : Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

CMR complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com