

CWR is transparent BOPP film for wrap around label applications. One sides is treated. The film has good mechanical, antistatic and slip properties.

APPLICATIONS

- Rotogravure and flexographic printing
- Hot melt receptive layer
- Single web structures



- Treated Layer
- OPP Layer
- OPP Core Layer
- OPP Layer
- Non Treated Layer

Properties		Typical Values			Method	Unit
Nominal Thickness		30	35	40	ITM	μm
Unit Weight		27,3	31,9	36,4	ITM	g/m²
Average Yield		36,6	31,4	27,5	ITM	m²/kg
Gloss (45°)		≥85			ASTM D 2457	Gloss unit
Haze		<2,5			ASTM D 1003	%
Treatment Level		≥38			ASTM D 2578	dynes/cm
Tensile Strength					ASTM D 882	N/mm²
	MD	140				
	TD	280				
Elongation at Break					ASTM D 882	%
	MD	180				
	TD	50				
Coefficient of Friction					ASTM D1894	
	B/B	≤0,35				
	B/M	≤0,25				
Thermal Shrinkage					ITM	130 °C 7 MIN
	MD	≤5,0				
	TD	≤3,0				

MD: Machine direction
TD: Transverse direction
B: Back
M: Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

CWR complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com