

OPA is white opaque BOPP film, both sides heat sealable, one side is treated. The film has outstanding whiteness and opacity, high gloss and excellent stiffness properties.

APPLICATIONS

- Well - suited for ice cream packaging, lamination and cold seal applications.



Properties	Typical Values	Method	Unit
Nominal Thickness	35 38	ITM	μm
Unit Weight	24,5 26,6	ITM	g/m ²
Average Yield	40,8 37,6	ITM	m ² /kg
Gloss (45°)	≥90	ASTM D 2457	Gloss unit
Opacity	min 80	ASTM D 1003	%
Treatment Level	≥38	ASTM D 2578	dynes/cm
Tensile Strength		ASTM D 882	N/mm ²
	MD 90 TD 200		
Elongation at Break		ASTM D 882	%
	MD 140 TD 38		
Coefficient of Friction		ASTM D1894	
<i>dynamic</i>	B/B ≤0,35 B/M ≤0,25		
Heat Seal Temperature	110 - 145		3 bar- 0,5 sec
Seal Strength	>2,0		130 C /3 bar/ 0,5 sec
Thermal Shrinkage		ITM	130 °C 7 MIN
	MD ≤5,0 TD ≤3,0		

MD: Machine direction
TD : Transverse direction
B : Back
M : Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

OPA complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com