

OPI is a white voided OPP film, matt on one side. Its special formulation results in a film with very high yield. The film is treated on both sides.



APPLICATIONS

- Outstanding opacity and whiteness
- Good antistatic properties, web flatness, machineability and die cutting
- High yield and orange peel effect
- Suitable for offset sheet fed printing with UV curing and oxidative drying inks.
- Suitable for gravure and UV-flexo printing
- For reel to reel printing with UV inks, inline Corona treatment is strongly recommended

Properties	OPI50	OPI55	OPI60	OPI65	Method	Unit
Nominal Thickness	50	55	60	65	ISO 4591	μm
Unit Weight	27,5	30,25	33	35,75	ISO 4591	g/m ²
Average Yield	36,4	33	30,3	28	ISO 4591	m ² /kg
Opacity			min. 88		DIN 53146	Gloss unit
Gloss (45°)			min. 65		ASTM D 2457	Gloss unit
Treatment Level			min. 38		ASTM D 2578	dynes/cm
Tensile Strength						
	MD		50		ASTM D 882	N/mm ²
	TD		100			
Elongation at Break						
	MD		120		ASTM D 882	%
	TD		30			

MD: Machine direction
TD : Transverse direction
B : Back
M : Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

OPI complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com