

SFI is a white voided OPP film, matt on one side, satin finish after injection. Its special formulation results in a film with very high yield. The film is treated on both sides.



APPLICATIONS

- Outstanding opacity and whiteness
- Good antistatic properties, web flatness, machineability and die cutting
- High yield and satin finish effect
- Suitable for offset sheet fed printing with UV curing and oxidative drying inks.
- Suitable for gravure and UV-flexo printing
- For reel to reel printing with UV inks, inline Corona treatment is strongly recommended

Properties	SFI60	SFI65	Method	Unit
Nominal Thickness	60	65	ISO 4591	μm
Unit Weight	37,2	40,3	ISO 4591	g/m ²
Average Yield	26,8	24,8	ISO 4591	m ² /kg
Opacity	min. 88		DIN 53146	Gloss unit
Gloss (45°)	min. 65		ASTM D 2457	Gloss unit
Treatment Level	min. 38		ASTM D 2578	dynes/cm
Tensile Strength				
MD	75		ASTM D 882	N/mm ²
TD	150			
Elongation at Break				
MD	130		ASTM D 882	%
TD	35			

MD: Machine direction
TD : Transverse direction
B : Back
M : Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

SFI complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com