

SWI is a solid white BOPP film, specifically developed for IML applications.

SWI is treated on both sides, one side is matt, one side is glossy.



APPLICATIONS

- Outstanding opacity and whiteness
- Good antistatic properties, web flatness, machineability and die cutting
- Glossy effect after injection moulding
- Suitable for offset sheet fed printing with UV curing and oxidative drying inks.
- Suitable for gravure and UV-flexo printing
- For reel to reel printing with UV inks, inline
- Corona treatment is strongly recommended

Properties	SWI50	SWI57	Method	Unit
Nominal Thickness	50	57	ISO 4591	µm
Unit Weight	48	54,7	ISO 4591	g/m ²
Average Yield	20,3	18,3	ISO 4591	m ² /kg
Opacity	>85	>90	DIN 53146	Gloss unit
Gloss (45°)	>55	>55	ASTM D 2457	Gloss unit
Treatment Level	min. 38		ASTM D 2578	dynes/cm
Tensile Strength	MD TD	120 210	ASTM D 882	N/mm ²
Elongation at Break	MD TD	180 30	ASTM D 882	%

MD: Machine direction
TD : Transverse direction
B : Back
M : Metal

*The data and figures provided in datasheet are intended to provide general information about our products .
They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications.*

STORAGE & HANDLING

The reels should be kept in their original packaging until used. It is recommended that films are stored below 30°C in order to minimize deterioration of film properties. All films should be allowed to reach operation room temperature for 24 hours before use.

*The treatment level declines with time.

FOOD CONTACT

SWI complies with EU and FDA regulations.

Polikon Plastik Film
Kemalpaşa OSB mah. 612 sok. No: 18 Kemalpaşa / İZMİR/TURKEY
Phone: +90 232 880 40 34 35
Fax: +90 232 880 40 33
www.polikonfilm.com