

TECHNICAL SPECIFICATION

HOT ROLLED COILED (HRC)
HRC.25.047-THP-(SAE1006)

No	Item	Specification	
1	Steel Grade	SAE1006 - AI	
2	Standard	J403:2024	
3	Width (mm)	900÷1650	
4	Width tolerance (mm)	+0/+20 (not include 20m each head and tail end)	
5	Thickness (mm)	W < 1250	1.20÷12.00
		W ≥ 1250	2.00÷25.40
	Thickness tolerance (mm)	±0.09	
6	Beyond thickness tolerance	The thickness tolerances shall apply to any point, but it is not less than 40mm from edge of hot rolled coil and not include 20m each head and tail end	
7	Chemical composition (%)	C	≤0.06% ✓
		Mn	≤0.20% ✓
		P	≤0.025% ✓
		S	≤0.015% ✓
		Si	≤0.030% ✓
		Cu	≤0.06% ✓
		Cr;Ni	≤0.06% ✓
		N	≤80 PPM ✓
		Al (Als)	100÷700 PPM ✓
8	Mechanical properties	Yield strength (MPa)	Min 195 Mpa ✓
		Tensile strength (MPa)	Min 270 Mpa ✓
		Elongation (%)	≥27 ✓
		Impact test (J)	- ✓
9	Camber	5mm/2000m length of strip, not include 20m each head and tail end	
10	Crown	≤80μm at the point 40mm from edge and not include 20m each head and tail end	
11	Wedge	≤50μm at the point 40mm from edge and not include 20m each head and tail end	
12	High spot	≤20μm	
13	Coil ID	762 (-40/+20) mm	
14	Coil OD	Max 2000mm	
15	Fishtail/ Tongue	Non skin-pass	Max 500mm each end
		Skin-passed	None
16	Edge condition	Mill edge; free from crack, saw tooth, bavia, ...	
17	Flatness tolerance	Non skin-pass	Max 20mm (not include 20m each head and tail end) ✓
		Skin-passed	Max 9mm (not include 15m each head and tail end) ✓
18	Telescope	Non skin-pass	Max 50mm ✓
		Skin-passed	Max 30mm ✓
19	Defect	Non skin-pass	Free from crack, hole, rolled in scale & sliver... (not include 20m each head and tail end) No coil break except 30m head and 50m tail end ✓
		Skin-passed	Uniform. No cracks, dents, scratches, fillers, scars with allowable size ≤ 0.01mm. No welding equipment, edge tearing. Cannot update the surface. Unnecessary, other unidentified images that affect the plating quality (not include 20m each head and tail end) ✓
20	Packing	As mill's standard	
21	Label	As mill's standard	
22	Coild Weigh	W: 900 ÷ 999	14 ÷ 18 ton
		W: 1000 ÷ 1099	16 ÷ 20 ton
		W: 1100 ÷ 1199	18 ÷ 22 ton
		W: 1200 ÷ 1299	18 ÷ 25 ton (aiming 22 ÷ 25 ton) ✓
		W: 1300 ÷ 1524	20 ÷ 25 ton
23	Grain size	07-11 (according to ASTM E112)	
24	Non - Metallic Inclusion	≤ Level 2 (according to ISO 4967)	
25	Finishing mill temperature (°C)	aiming ≤ 900 (±20°C)	
26	Coiling temperature (°C)	Thickness ≤2.45 mm min Coiling temperature DQ 1 aiming ≥660 (±20°C), DQ2 680 (±20 °C) ✓	

THP

HPDQ

Ngô Quang Hồng

OS2511166999



hp 11/125