Quantifying Precious Metal Loss in E-Waste: A Comprehensive Source-Based Analysis of Gold and Silver Recovery Potential in India, West Bengal, and Kolkata with Component-Level Targeting and Institutional Source Mapping

SUBHAM DAS[a,1]

[a]Urban Gold India, Kolkata, West Bengal

This manuscript was compiled on February 4, 2026

Electronic waste (e-waste) represents both a significant environmental challenge and an untapped resource for precious metal recovery. This comprehensive study quantifies the mass and precious metal content of unmanaged printed circuit boards (PCBs) across India, West Bengal, and Kolkata using documented e-waste generation data (India: 1,601,155 t/yr FY21–22) and literature-based metal concentration ranges validated across multiple metallurgical characterization studies. We estimate that nationally, 118–206 tonnes/day of PCBs are being dumped or informally processed, containing 4.6–188 kg/day of gold depending on product mix scenarios (conservative mixed PCBs: 39.19 g Au/t vs. mobile-phone-rich: 860–1,600 g Au/t). Mobile phone PCBs emerge as the richest source per unit mass, followed by desktop motherboards, server equipment, and telecommunications infrastructure. Component-level analysis identifies gold wire bonds, plated connectors (SIM contacts, USB pins, gold fingers), and backplane boards as priority recovery targets. Institutional sources including data centers (CtrlS: 0.47–1.2 g Au/day, Nxtra: 0.33–0.85 g Au/day), IT campuses (TCS Rajarhat: 0.38–0.55 g Au/day, Infosys: 0.10–0.14 g Au/day), and telecom operators (Airtel: 0.12–0.24 g Au/day, Jio: 0.17–0.35 g Au/day) collectively contribute 1.6–3.3 g Au/day in Kolkata alone. Geographic hotspots are mapped for Kolkata (Khidderpore–Metiabruz, Chandni Market, Topsia–Tiljala, Ghusuri) and nationally (Delhi's Seelampur/Mustafabad, Mumbai's Dharavi, Bengaluru's Peenya). National telecom analysis across India's top 8 metros reveals 19.7–23.4 tonnes PCBs/year containing 1.2–2.8 kg Au, with recovery scenarios demonstrating that 90% formal capture could recover 1.08–2.52 kg Au/year with minimal logistical burden. We provide field-ready sampling protocols (6-site design with ICP-MS analysis specifications), component-specific separation guidelines, and telecom-specific recovery SOPs to transform these estimates into operational recovery programs. Metal usage vs. value analysis confirms copper as the most-used metal by mass (200–320 kg/t PCB) while gold dominates economic value (5.5–6.0 crore/kg vs. 700–900/kg for copper), establishing combined copper-gold recovery as the optimal economic model for sustainable urban mining in India.

E-waste | Urban Mining | Precious Metals Recovery | Gold Recovery | PCB Recycling | Circular Economy | Institutional E-waste | Telecom Equipment Recovery | Mobile Phone Recycling

Electronic waste has become one of the fastest-growing waste streams globally, with India generating approximately 1.601 million tonnes annually as of FY 2021–22 according to official government data. Within this massive waste stream lies a concentrated repository of valuable metals, particularly in printed circuit boards (PCBs) which constitute only 4–7% of e-waste by mass but contain the lion's share of precious metals and monetary value. Despite representing significant economic value—potentially billions of rupees annually in recoverable gold alone—and posing substantial environmental risk through toxic metal release, the vast majority of India's e-waste (approximately 67% nationally and over 99.8% in West Bengal) remains unmanaged by formal recycling infrastructure, instead flowing through informal dismantling networks where recovery is inefficient (30–60% vs. >95% in formal facilities), environmentally destructive (open burning, uncontrolled acid baths), and results in permanent loss of strategic materials.

This research addresses critical knowledge gaps: quantifying precisely how much precious metal-bearing material is being lost daily in India's informal e-waste streams, identifying which devices and components contain the most valuable metals with specific concentration ranges, mapping both geographic hotspots and institutional sources of high-grade e-waste, and providing actionable recovery protocols. By establishing evidence-based baselines for PCB mass flows and

Significance Statement

This study quantifies daily precious metal losses from unmanaged printed circuit boards (PCBs) in India's e-waste stream, revealing that 118–206 tonnes/day of PCBs containing 4.6–188 kg/day of gold are being lost nationally depending on product mix. By identifying mobile phones and small IT devices as the highest-value targets (340–1,600 g Au/tonne vs. 39 g Au/tonne for mixed PCBs) and mapping institutional sources (data centers, telecom operators, IT campuses contributing 1.6–3.3 g Au/day in Kolkata alone), we demonstrate that formal recovery from centrally-managed assets could recover kilograms of gold daily with minimal behavioral change. We provide field-ready sampling protocols, component-specific targeting recommendations, and recovery scenarios showing 90% formal capture of telecom equipment alone could recover 1.08–2.52 kg Au/year from India's top 8 metros, providing actionable priorities for urban mining policy and circular economy implementation.

Single author research compilation, analysis, modeling, and protocol development.

No conflicts of interest declared.

To whom correspondence should be addressed. E-mail: researcher@email.com

precious metal content across national, state, and city scales using transparent, reproducible modeling assumptions, we provide the foundation for targeted urban mining interventions that can shift India from resource loss to resource recovery.

Methods and Data Sources

E-Waste Generation Data. Our analysis uses official FY 2021–22 e-waste generation figures:

India (national): 1,601,155.36 tonnes/year from government documentation

West Bengal (state): 168,563 tonnes/year calculated using CEEW 1.7 kg/capita baseline applied to state population

Kolkata (district): 8,483 tonnes/year derived from Kolkata Metropolitan Area projections

These figures represent documented generation; actual generation may be higher due to unreported flows.

PCB Fraction and Metal Content. PCB fraction of e-waste by mass: We apply a range of 4–7% based on multiple literature sources (Wang 2012; Das et al.) that place PCBs in this range across diverse e-waste streams. This accounts for variability in product mix.

Unmanaged share: National documented formal processing in FY21–22 was 527,132 t/yr, leaving 1,074,024 t/yr (67.08%) unmanaged. For West Bengal, documented formal processing was only 320 t/yr, yielding approximately 99.8% unmanaged. For Kolkata, field studies indicate 90% informal handling.

Metal concentration scenarios: We present two anchored scenarios based on peer-reviewed metallurgical characterization studies:

Scenario A—Conservative Mixed PCBs: Au = 39.19 g/t, Ag = 22.89 g/t (MDPI 2024 aggregation of mixed motherboards)

Scenario B—Mobile-Phone-Rich PCBs: Au = 860–1,600 g/t, Ag = 140–5,800 g/t (Zhou/Tan 2021; Annamalai 2021; multiple mobile PCB characterization studies)

These scenarios bracket uncertainty arising from unknown product mix composition. The true daily metal loss depends heavily on the fraction of discarded equipment that is mobile phones vs. large appliances.

Institutional Modeling Assumptions. For company-specific estimates where public disclosure is unavailable, we employ equipment-inventory-based modeling:

IT Services Firms:

- Laptops/desktops: 1 per employee, 4-year refresh (25% replaced annually)
- Phones: 1 per employee, 2.5-year refresh (40% replaced annually)
- Phone PCB mass: 30 g per unit
- Laptop/desktop PCB mass: 300 g per unit

Data Centers:

- Server refresh: 4–5 years (20–25% annually)
- Network gear refresh: 5 years (20% annually)
- Server PCB mass: 1.5–2.0 kg per unit
- Network gear PCB mass: variable by type

Telecom Infrastructure:

- Core/aggregation gear refresh: 7–8 years (14% annually)
- Base station electronics refresh: 6–7 years (15% annually)
- Core switch PCB mass: 4–6 kg per unit
- Base station electronics PCB mass: 1.0–1.5 kg per site
- Telecom PCB gold concentration: 60–120 g Au/t (higher than office IT due to thick reliability plating)

All assumptions are conservative and aligned with industry standard practice. Uncertainties are explicitly bracketed with ranges rather than point estimates.

National, State, and District PCB Mass Flows

PCB Mass Generation and Unmanaged Flows. Table 1 presents calculated PCB generation and unmanaged flows across geographic scales.

Table 1. PCB Mass Flows: Generation and Unmanaged Portions

Region	PCB Generated (t/day)	PCB Unmanaged (t/day)	Unmanaged Share (%)
India (National)			
4% PCB fraction	175.5	117.7	67.08
7% PCB fraction	307.1	206.0	67.08
West Bengal (State)			
4% PCB fraction	18.47	18.44	99.8
7% PCB fraction	32.33	32.27	99.8
Kolkata (District)			
4% PCB fraction	0.93	0.837	90.0
7% PCB fraction	1.63	1.464	90.0

Key Finding: Nationally, 118–206 tonnes/day of PCBs escape formal processing. West Bengal's near-total informal processing (99.8% unmanaged) represents a severe infrastructure deficit. Kolkata's 0.84–1.46 t/day unmanaged PCBs concentrate across mapped hotspot clusters.

Precious Metal Content: Two-Scenario Analysis. Tables 2 and 3 present gold and silver content under conservative and mobile-rich scenarios.

Interpretation: The >20-fold difference between scenarios (4.6–8.1 kg Au/day vs. 101–188 kg Au/day nationally) demonstrates that product mix measurement is the single most critical uncertainty. If the unmanaged PCB stream contains substantial mobile phone components, national daily gold loss could reach hundreds of kilograms. If dominated by larger, older motherboards and household electronics, gold loss is measured in single-digit kg/day.

Component-Level Analysis: Precious Metal Distribution

Gold Distribution by Component Type. Precious metals concentrate overwhelmingly in specific components within e-waste. Our synthesis of metallurgical characterization studies identifies the following hierarchy:

Table 2. Scenario A: Conservative Mixed PCB Metal Content (Au = 39.19 g/t; Ag = 22.89 g/t)

Region	PCB Unmanaged (t/day)	Gold (Au) (kg/day)	Gold (Au) (t/year)	Silver (Ag) (kg/day)
India (National)				
Low (4% PCB)	117.7	4.61	1.68	2.69
High (7% PCB)	206.0	8.07	2.95	4.71
West Bengal (State)				
Low (4% PCB)	18.44	0.057	0.0209	0.033
High (7% PCB)	32.27	0.112	0.0409	0.074
Kolkata (District)				
Low (4% PCB)	0.837	0.033	0.012	0.019
High (7% PCB)	1.464	0.057	0.021	0.033

Table 3. Scenario B: Mobile-Phone-Rich PCB Metal Content (Au = 860–1,600 g/t; Ag = 140–5,800 g/t)

Region	PCB Unmanaged (t/day)	Gold (Au) (kg/day)	Gold (Au) (t/year)	Silver (Ag) (kg/day)
India (National)				
Low mobile range	117.7	101	37	16–683
High mobile range	206.0	188	69	(wide range)
West Bengal (State)				
Low mobile range	18.44	1.26	0.46	0.205–167
High mobile range	32.27	2.34	0.85	(wide range)
Kolkata (District)				
Low mobile range	0.837	0.72	0.26	0.19–8.49
High mobile range	1.464	2.34	0.85	(wide range)

Highest Gold Concentration Components. **Gold wire bonds inside IC packages:** Extremely thin gold wires (or gold ball bonds) connect semiconductor die to package leads. While each bond contains picograms of gold, modern ICs can contain hundreds to thousands of wire bonds, and aggregate processing of millions of ICs yields significant gold mass. Concentration when isolated: essentially pure gold, but requires chemical de-packaging.

Mobile phone PCBs and modules: Central literature value 340 g Au/t for mixed mobile phone waste (Annamalai 2021); reported ranges 142–700 g/t depending on model and sampling methodology (Kasper 2018); extreme targeted samples of phone PCB fragments report up to 1,600 g/t (Zhou 2021). Mobile phones are consistently the richest per-tonne e-waste source.

Gold-plated connectors and contact surfaces:

- SIM card contacts and SIM tray pads
- USB/USB-C/micro-USB connector pins
- HDMI, RJ-45, audio jack contacts
- RF coaxial connectors
- Battery connector pads
- Cradle/docking contacts

Gold plating thickness typically ranges 0.05–1.27 m (2–50 microinches). While each connector has minimal gold mass, cumulative mass across thousands of units becomes economically significant.

PCB edge connectors ("gold fingers"): Found on RAM sticks, PCIe/PCI expansion cards, and various modules. Deliberately gold-plated for insertion wear resistance and low contact resistance. Industry-standard plating specifications provide reliable gold content when batch processing.

High Gold Concentration Components. **Desktop/server motherboards:** Mixed motherboard averages 39.19 g Au/t (MDPI 2024 aggregation of 10 models), but high-end boards with many expansion slots, CPU socket pins, and RAM slots can reach hundreds g/t. Server backplanes with dense connector arrays can exceed 200 g/t.

Telecommunications infrastructure PCBs: Core switches, routers, optical transport equipment, and base station controllers feature thick gold plating for high-reliability applications. Estimated range: 60–120 g Au/t for telecom-grade PCBs, with backplane boards at the high end.

ENIG and hard-gold PCB surface finishes: Electroless Nickel Immersion Gold (ENIG) is common on modern high-end PCBs. While thickness is extremely thin (gold flash), total surface area on multi-layer boards contributes measurable gold in aggregate processing.

Moderate to Low Gold Components. **Laptop motherboards, camera PCBs, consumer electronics:** Moderate amounts, typically single-digit to tens g/t depending on model and connector density.

Large household appliances: Motors, compressors, CRT glass, most plastics contain negligible precious metals. Copper dominates these streams.

Silver Distribution. **Photovoltaic (PV) cells:** Silver paste on PV cells represents the highest-concentration source—several tens to hundreds g/t in PV modules depending on cell technology.

Mobile phone PCBs: Some datasets report 3.5 kg Ag/t (3,500 g/t) for mobile phone waste, though this is highly variable across studies.

Silver-bearing solders and contacts: Moderate concentrations in switch contacts, relay blades, and certain solder alloys (modern lead-free solders may use silver).

Table 4. Device Types: Primary Valuable Components and Target Metals

Device Type	Primary Precious-Metal Parts	Valuable Metals (Priority Order)
Mobile phones / Smartphones	PCB (logic board), SIM contacts, connectors, IC wire bonds, camera module contacts, USB pins	Au (very high), Ag (moderate), Pd (low), Cu (bulk), Nd (magnets/speakers)
Desktop PC	Motherboard, expansion cards (PCIe, PCI), CPU socket pins, RAM gold fingers, HDD magnets	Au (moderate), Pd (moderate), Cu (high), Nd (HDD magnets)
Laptops / Notebooks	Motherboard, connectors, HDD, SSD connectors, keyboard contacts	Au (moderate), Ag (low-moderate), Cu (high), Nd (HDD magnets)
Servers / Data centers	Backplanes, CPU sockets, RAM modules, NIC cards, blade connectors, high-density PCBs	Au (moderate-high), Pd (moderate), Cu (very high)
Telecom infrastructure	Core switches/routers, line cards, backplane boards, optical transport equipment, base station controllers	Au (moderate-high, thick plating), Cu (very high), Pd (low-moderate)
Printers / Peripherals	Motors, circuit boards, connector assemblies	Cu (motors, high), Au (small), Ag (contacts, small)
TVs / Set-top boxes	Main PCBs, power supplies, minimal connectors	Cu (bulk), Au (low-moderate), Ag (low)
LED / LCD displays	ITO layers (indium), driver PCBs, backlighting	In (small but valuable), Au/Ag (small in drivers)
Photovoltaics (PV)	PV cell silver paste, junction contacts, mounting hardware	Ag (high in PV cells), small Au in contacts
HDDs, speakers	NdFeB magnets, voice coils, PCB controllers	Nd (rare earth magnets), Cu (voice coils), Au (controller PCB, small)
Large white goods (refrigerators, washing machines)	Motors, compressors, minimal electronics	Cu (high), negligible Au/Ag

Printed circuit patterns: Some older PCBs used silver-bearing inks or coatings.

Other Valuable Metals. Palladium (Pd): Found in multilayer ceramic capacitors (MLCCs), certain IC platings, and specialized connectors. Mobile phone waste studies report 140 g Pd/t. Lower mass than gold but strategically important.

Copper (Cu): Dominates by mass—100–300 kg/t in PCBs (often 100,000–300,000 g/t). Backbone metal providing structural conductivity. Present in wiring, cables, power supplies, motors, PCB copper layers.

Neodymium (Nd) and rare earth elements: Concentrated in neodymium-iron-boron (NdFeB) magnets found in hard disk drives, loudspeakers, and some motors. Small overall mass per tonne of mixed e-waste but high strategic value.

Indium (In): Present in LCD/flat panel displays as indium tin oxide (ITO). Approximately 200–260 g/t of display glass. Very valuable per kg but difficult to recover economically at scale with current technology.

Tin (Sn): Major solder metal (10–40 kg/t in PCBs). Ubiquitous but modest value (2,500–3,000/kg).

Device-to-Component Mapping. Table 4 provides a practical guide linking device types to valuable components and priority metals.

Quantifying Gold in Top-Priority Components

To refine national estimates, we modeled gold content specifically in the two highest-value component classes: (1) mobile phone PCBs and (2) gold fingers/connector pins on non-phone PCBs. This focuses on mechanically separable, high-recovery-yield components.

Modeling Assumptions.

- Phone PCB share of total PCB mass: Low 5%, Central 10%, High 20%
- Gold in phone PCBs: Low 142 g/t, Central 340 g/t, High 1,000 g/t
- Gold in fingers/pins on non-phone PCBs: Low 5 g/t, Central 15 g/t, High 50 g/t

These parameters span conservative to phone-heavy scenarios and account for variability in literature-reported concentrations.

Results: Gold in Priority Components. Table 5 presents daily gold content in these targeted component streams.

Table 5. Gold in Priority Components: Phone PCBs + Fingers/Pins

Region	Min (kg Au/day)	Central (kg Au/day)	Max (kg Au/day)
India	1.395	7.688	49.440
West Bengal	0.219	1.204	7.745
Kolkata	0.00995	0.0546	0.3504

Central Estimate Interpretation: Under central assumptions (phone PCBs = 10% of PCB mass, phone Au = 340 g/t, fingers = 15 g/t), India loses approximately 7.7 kg of gold per day (2.8 tonnes/year) in just these two component classes from unmanaged PCB streams. West Bengal loses 1.2 kg/day (0.44 t/year), and Kolkata loses 54.6 g/day (19.9 kg/year).

The maximum scenario (phone-heavy feedstock with very high Au concentration) suggests national daily loss could approach 50 kg Au/day in these priority components alone. The minimum scenario still shows measurable daily losses (1.4 kg nationally).

Geographic Hotspots: Informal Processing Clusters

E-waste containing high-value PCBs congregates in well-documented informal processing hotspots where manual dismantling, crude recovery, and dealer networks concentrate material flows.

Kolkata Metropolitan Area Hotspots. Based on West Bengal Pollution Control Board field assessments and site mapping:

Chandni Market / Princep Street / Grey Street: Second-hand computer and peripherals trade hub. Large volume of motherboards, expansion cards, and RAM modules (gold fingers, edge connectors). Active dealer networks sort and grade PCBs.

Khidderpore–Metiabruz: Historic scrap market and second-hand mobile phone hub. High concentration of mobile phone dealers, repairers, and dismantlers. Phone modules, SIM contacts, and connector parts move through this cluster. Critical for mobile-phone PCB sampling.

Topsia–Tiljala / Kankurgachi–Kapdapara–Phool Bagan: Scrap recycling and small-scale processors focusing on copper recovery and some plating separation. Mixed PCB processing with open burning and acid baths reported.

Hazra Crossing / Bondel Gate / Rifle Range Road / Keshav Sen Street / Tarak Pramanick Road / Girish Park: Local clusters for copper smelting and PCB preconcentration. Some mechanical separation (de-population of components) before chemical processing.

Howrah (Ghusuri, Bajrangbali): TV and large electronics dismantling. Lower precious metal concentration but high volume throughput.

These KMA hotspots represent the geographic concentration points where Kolkata's 0.84–1.46 t/day of unmanaged PCBs flow. They are priority sites for sampling, intervention, and formalization programs.

National Hotspot Map. Delhi–NCR (largest national hub): Seelampur (Old and New), Mustafabad, Turkman Gate, Daryaganj, Mandoli, Jafrabad, Mayapuri, Okhla border areas, Brijpuri, Seemapuri. Toxics Link mapping identified 15 major hotspots across Delhi-NCR. Seelampur and Mustafabad are the largest, drawing e-waste from across northern India. Crude recovery methods (open burning, acid leaching) are widespread with significant environmental and health impacts.

Mumbai and Maharashtra: Dharavi (multiple subclusters), Kamla Nagar, Sheshwadi areas, eastern suburbs (Wadala, Mankhurd). Mumbai region is historically the single largest e-waste generator and processor in India. Well-established scrap dealer networks and informal recycling clusters.

Bengaluru: Peenya industrial area and other local recycling/wholesale hubs. Industrial belt supplies manufacturing rejects and device discards. Mix of formal authorized recyclers and informal processors in proximity.

Other major cities: Chennai, Hyderabad, Pune, and Ahmedabad all have documented informal clusters or dump/dismantling spots, though less extensively mapped than Delhi, Mumbai, and Bengaluru.

These geographic concentrations enable targeted intervention: establishing pre-processing hubs, conducting sampling campaigns, and engaging informal networks in these specific locations can achieve disproportionate impact relative to dispersed interventions.

Institutional Sources: Modeled Estimates

Large institutional generators represent a fundamentally different opportunity than household e-waste: centrally managed assets with predictable replacement cycles, documented inventories, and existing asset disposition processes. These characteristics enable formal collection with minimal behavioral friction.

IT Services Campuses (Kolkata). Tata Consultancy Services—Rajarhat / New Town Campus

Site parameters: 20,000 employees (modeled central estimate based on public campus scale information)

Annual discarded devices:

- Laptops/desktops (25% replacement/year): 5,000 units
- Phones (40% replacement/year): 8,000 units

PCB mass/year:

- Phones: 8,000 × 0.03 kg = 240 kg
- Laptops/desktops: 5,000 × 0.3 kg = 1,500 kg
- Total: 1.74 tonnes PCB/year

Gold content:

- Phones: 0.24 t × 340 g/t = 81.6 g Au
- IT boards: 1.5 t × 40–80 g/t = 60–120 g Au
- **Total: 0.14–0.20 kg Au/year (0.38–0.55 g Au/day)**

Infosys—Kolkata Office

Site parameters: 5,000 employees (modeled)

Annual discarded devices:

- Laptops/desktops: 1,250 units
- Phones: 2,000 units

PCB mass/year: 0.44 tonnes

Gold content: **0.035–0.050 kg Au/year (0.10–0.14 g Au/day)**

Data Centers (Kolkata / New Town). CtrlS—New Town Data Centre

Site parameters: 50 MW campus (phased deployment); 10,000 active servers modeled for conservative phase-1 scale

Annual hardware retirement:

- Servers (25% replacement/year): 2,500 units
- Network gear: 500 units

PCB mass/year:

- Servers: 2,500 × 1.5–2.0 kg = 3.75–5.0 t
- Network gear: 0.5 t
- Total: 4.25–5.5 t PCB/year

Gold content:

- 4.25–5.5 t × 40–80 g/t = 170–440 g Au/year
- **Total: 0.17–0.44 kg Au/year (0.47–1.2 g Au/day)**

Nxtra—Kolkata / New Town

Site parameters: 7,000 active servers (modeled)

Annual retirement: 1,750 servers, 350 network gear units

PCB mass/year: 3.0–3.9 tonnes

Gold content: **0.12–0.31 kg Au/year (0.33–0.85 g Au/day)**

Data centers emerge as the highest-concentration institutional gold sources per unit area. Dense, high-layer server boards with gold-plated backplane connectors and NICs yield moderate but steady precious metal flows.

Telecom Operators (Kolkata). Bharti Airtel—Kolkata Switching and Network Centers

Estimated asset base (Kolkata metro):

- Core / aggregation switches: 350–450 units
- Base stations served: 1,800
- OLT / optical gear: 400 units

Annual retirement (14–15% refresh rates):

- Core/aggregation: 56 units
- Base station electronics: 270 units
- Optical/network gear: 60 units

PCB mass/year: 0.72 tonnes

Gold content (telecom PCBs: 60–120 g Au/t): **0.043–0.086 kg Au/year (0.12–0.24 g Au/day)**

Reliance Jio—Kolkata Switching and Network Centers

Estimated asset base (Kolkata metro, denser 4G/5G network):

- Core / aggregation switches: 500–650 units
- Base stations (macro + small cells): 2,500
- Optical / cloud-native gear: 600 units

PCB mass/year: 1.05 tonnes

Gold content: **0.063–0.126 kg Au/year (0.17–0.35 g Au/day)**

Consolidated Institutional Gold (Kolkata). Table 6 summarizes modeled institutional contributions.

Table 6. Institutional Gold Generation (Kolkata)

Organization	Sector	Au (kg/yr)	Au (g/day)
TCS Rajarhat	IT Services	0.14–0.20	0.38–0.55
Infosys Kolkata	IT Services	0.035–0.050	0.10–0.14
CtrlS New Town	Data Center	0.17–0.44	0.47–1.20
Nxtra Kolkata	Data Center	0.12–0.31	0.33–0.85
Airtel Kolkata	Telecom	0.043–0.086	0.12–0.24
Jio Kolkata	Telecom	0.063–0.126	0.17–0.35
Total	—	**0.57–1.21**	**1.6–3.3**

Key Finding: Kolkata's major institutional generators collectively contribute 1.6–3.3 g Au/day before counting household mobile phones, retail returns, or informal market inflows from surrounding regions. Data centers provide the highest concentration per facility.

National Telecom Recovery Potential

We extended telecom modeling to India's 8 largest metros to quantify national-scale recovery opportunities from this centrally-managed sector.

Metro-Level Telecom Network Scale. Table 7 presents modeled network assets for Airtel + Jio combined across metros.

National Telecom PCB Flows and Gold Content. Table 8 presents calculated annual PCB retirement and gold content.

National Telecom Gold Leakage (Top 8 Metros Only): 1.2–2.8 kg gold per year, or 3.3–7.7 g gold per day. This is a lower-bound urban estimate excluding smaller cities, rural infrastructure, manufacturing rejects, and imported used equipment.

Capture Efficiency Scenarios. Table 9 models gold recovery under improved formal capture rates.

Policy Implication: Achieving 90% formal capture nearly eliminates telecom gold loss in major metros while requiring no consumer participation—only improved asset disposition protocols at telecom operator facilities. This represents one of the fastest-deployment pathways for urban mining in India.

Copper vs. Gold: Usage vs. Value Analysis

A fundamental question in e-waste recovery economics is which metal matters most. The answer depends on whether the metric is mass (usage) or economic value.

Most-Used Metal by Mass: Copper. Copper unambiguously dominates by mass:

- PCB copper content: 200–320 kg/tonne (20–30% by mass)
- Present in: wiring, cables, motors, power supplies, PCB traces and power planes, heat sinks
- Value: 700–900/kg (USD 8–11/kg)
- Functional role: No electronic device operates without copper—it is the structural skeleton of all electronics

Copper provides the largest bulk economic stream in e-waste recycling and establishes baseline operational viability for recovery facilities.

Most-Valuable Metal by Economic Density: Gold. Gold unambiguously dominates by value per kilogram:

- PCB gold content: 30–50 g/tonne (mixed), 150–1,000+ g/tonne (mobile phones)
- Value: 5.5–6.0 crore/kg (USD 158,000/kg)
- Economic reality: A few grams of gold are worth more than hundreds of kilograms of copper
- Functional role: Used only where failure is unacceptable—contacts, connectors, wire bonds—due to corrosion immunity and reliability

At current prices, recovering even 1 kg of gold per day nationally generates 5.5–6.0 crore daily revenue (USD 1.9–2.1 million), or 2,000–2,200 crore annually (USD 700–770 million).

Other Metals: Strategic Position. Table 10 provides comparative analysis across key metals.

Optimal Recovery Strategy: Combined copper-gold recovery establishes economically sustainable operations. Copper provides steady bulk revenue and justifies collection infrastructure. Gold provides profit margin and makes targeted collection of high-grade feedstocks (phones, servers) financially compelling.

Table 7. Telecom Network Scale by Metro (Airtel + Jio Combined)

Metro	Core/Aggregation Units	Base Stations	Metro Class
Delhi	1,200–1,400	4,000–5,000	Mega
Mumbai	1,200–1,400	4,000–5,000	Mega
Bengaluru	700–900	2,500–3,000	Tier-1
Chennai	700–900	2,500–3,000	Tier-1
Hyderabad	700–900	2,500–3,000	Tier-1
Pune	450–650	1,800–2,500	Tier-2 Large
Kolkata	450–650	1,800–2,500	Tier-2 Large
Ahmedabad	450–650	1,800–2,500	Tier-2 Large

Table 8. Telecom PCB Flows and Gold Content (Top 8 Metros, Airtel + Jio)

Metro	PCB Discarded (t/year)	Gold Leaked (kg/year)	Gold Leaked (g/day)	Silver Range (g/year)
Delhi	3.8–4.5	0.23–0.54	0.63–1.48	Variable
Mumbai	3.9–4.6	0.24–0.55	0.66–1.50	Variable
Bengaluru	2.6–3.1	0.16–0.37	0.44–1.01	Variable
Chennai	2.4–2.9	0.14–0.35	0.38–0.96	Variable
Hyderabad	2.3–2.8	0.14–0.34	0.38–0.93	Variable
Pune	1.6–2.0	0.10–0.24	0.27–0.66	Variable
Kolkata	1.7–1.8	0.11–0.21	0.29–0.59	Variable
Ahmedabad	1.4–1.7	0.08–0.20	0.22–0.55	Variable
TOP-8 TOTAL	**19.7–23.4**	**1.20–2.80**	**3.3–7.7**	—

Table 9. Telecom Gold Recovery Scenarios (Top 8 Metros)

Capture Efficiency	Gold Recovered (kg/year)	Gold Still Leaking (kg/year)
30%	0.36–0.84	0.84–1.96
60%	0.72–1.68	0.48–1.12
90%	1.08–2.52	0.12–0.28

Field Sampling and Assay Protocol

The primary uncertainty in our estimates—product mix of discarded PCBs—can be resolved through systematic field sampling. We provide a complete, field-ready protocol.

Sampling Plan Design. **Site Selection:** 6 representative hotspots per city

For Kolkata:

1. Khidderpore–Metiabruz (mobile phone hub)
2. Chandni Market / Princep Street (computer/peripheral trade)
3. Topsia–Tiljala (scrap recycling cluster)
4. Ghusuri, Howrah (large electronics dismantling)
5. Rajarhat municipal transfer station (institutional waste entry point)
6. One additional peri-urban collection point

Sample Collection per Site:

- Whole devices:
  - n=30 mobile phones (varied models)
  - n=10 laptops (varied brands/ages)
  - n=10 desktop motherboards
- Depopulated PCB fragments: composite sample representing 10–20 kg bulk PCBs

Temporal Coverage: 3-month sampling period to capture seasonal and flow variations

Sample Preparation.

1. Manual dismantling to isolate:
   - Complete PCBs from devices
   - Connector assemblies (separate)
   - IC packages (for wire bond analysis if resources permit)
2. Grind representative sub-sample to <2 mm particle size for homogeneity
3. Prepare composite samples ensuring representativeness
4. Document masses at each stage (whole device, PCB mass, prepared sample mass)

Analytical Methods. **Primary Method:** ICP-MS (Inductively Coupled Plasma Mass Spectrometry)

Alternative (lower cost): ICP-OES (Optical Emission Spectroscopy) with reduced sensitivity for trace elements

Digestion Protocol:

- Complete digestion using aqua regia (3:1 HCl:HNO) or
- Microwave-assisted digestion for improved efficiency and safety
- Ensure complete dissolution of metals

Target Analytes: Au, Ag, Pd, Pt, Cu, Sn, Pb, Ni, Zn, In, Nd (rare earths as available)

Quality Assurance/Quality Control:

Table 10. Metal Comparison: Usage vs. Value in E-Waste

Metal	Concentration (typical PCB)	Value (/kg)	Usage (Mass)	Value (Economic)	Strategic Importance
Copper (Cu)	200–320 kg/t	700–900			Structural backbone
Gold (Au)	30–1,000 g/t	5.5–6.0 crore			Economic driver
Silver (Ag)	20–3,500 g/t	70,000–80,000			Bulk precious metal
Palladium (Pd)	<1–200 g/t	4–5 crore			Strategic PGM
Tin (Sn)	10–40 kg/t	2,500–3,000			Solder metal
Nickel (Ni)	Variable	Moderate			Plating/alloys
Indium (In)	200–260 g/t (displays)	20–30 lakh			Display technology
Nd / REEs	Variable (magnets)	High			Strategic future

- Certified Reference Materials (CRMs): Process at least 1 CRM per batch (e.g., NIST SRM for electronic materials)
- Method blanks: 1 per 10 samples
- Duplicate samples: 10% of total samples
- Spike recoveries: Add known quantities to verify recovery efficiency (target >95% for Au, Ag, Pd)
- Method detection limits: Document and report MDLs for all analytes
- Inter-laboratory checks if multiple labs involved

Reporting Format. Results should include:

- Concentration per device type (mg/kg or g/t)
- Concentration per component (PCB, connector assembly, IC package)
- Mass-weighted per-tonne values with 95% confidence intervals
- Statistical analysis:
  - Mean, median, standard deviation
  - Range (min–max)
  - Coefficient of variation
  - Distribution plots for major metals
- Recovery efficiency data (spike recoveries)
- Blanks and detection limits

Estimated Costs and Timeline. For 6 sites × 120 samples (50 devices + 6 bulk composites per site):

- Sample collection and preparation: 2–3 months
- ICP-MS analysis (commercial lab): 3,000–5,000 per sample for multi-element suite
- Total analytical costs: 3.6–6.0 lakh
- Additional: CRMs, consumables, transportation: 1–2 lakh
- **Total estimated budget: 4.6–8.0 lakh**

This investment converts literature ranges into locally validated, defensible numbers suitable for business case development and policy formulation.

Component-Specific Recovery SOP

Maximizing gold recovery requires component-specific protocols matched to feedstock characteristics.

Mobile Phones and High-Grade PCBs. Target Components (Pull List):

- Complete logic board (main PCB)
- SIM card contacts and tray
- Camera module PCBs
- USB/charging port assemblies
- All visible connector assemblies
- IC packages if de-packaging is economical

Pre-Processing:

1. Manual disassembly to remove batteries, screens, housings
2. Separate PCB from mechanical components
3. Remove high-value connectors intact (for concentrated processing)
4. Store boards in dry, labeled containers to prevent oxidation

Expected Yield: 340–1,600 g Au/tonne PCB
Recommended Processing: Hydrometallurgical leaching or proprietary room-temperature chemistry (Royal Mint model) achieving >95% gold recovery

Desktop/Server Motherboards and IT Equipment. Target Components:

- RAM gold fingers (edge connectors)
- CPU socket pins and contacts
- Expansion card edge connectors (PCIe, PCI)
- Backplane connector assemblies
- High-density PCB sections with many connectors

Pre-Processing:

1. De-populate valuable components (RAM, CPUs, expansion cards) before bulk processing
2. Mechanical separation: remove heat sinks, fans, non-PCB materials

3. If resources permit, separate high-connector-density sections from low-value board areas

4. Shred remaining boards to <5 cm fragments for density separation

Expected Yield: 40–125 g Au/tonne mixed motherboards; high-end server boards can reach 200+ g/t

Recommended Processing: Mechanical separation (eddy current for metals, density separation) followed by hydrometallurgical recovery of concentrated fractions

Telecom Equipment (Operator-Specific SOP). Highest Priority Components:

- Core router and switch line cards (thick gold plating)
- Backplane boards (high-reliability, high-gold plating)
- Optical transport boards (DWDM, OLT, ROADM equipment)
- NIC and transceiver host boards
- Base station BBU controller boards

Medium Priority:

- Power distribution boards with gold-plated connectors
- Control and management PCBs

Do NOT Prioritize for Gold:

- Metal enclosures and chassis (scrap metal value only)
- Heat sinks (aluminum scrap)
- Cables (copper recovery only)

Pre-Processing Rules:

1. Remove boards intact—avoid shredding whole units
2. Segregate by equipment type:
    - Core/backplane boards (highest value)
    - Access/network boards
    - Power supply boards (lower precious metal)
3. Remove batteries and large capacitors separately (hazmat)
4. Store in dry, labeled crates organized by board type

Expected Yield: 60–120 g Au/tonne telecom PCBs; backplane boards at high end of range

Recommended Processing Pathway:

1. Mechanical depopulation of ICs and connectors where economical
2. Hydrometallurgical recovery with closed-loop reagent systems
3. Avoid: open burning (loses gold to fumes), uncontrolled acid baths (environmental damage, incomplete recovery)

Documentation for EPR Compliance. All institutional sources should maintain:

- Board counts by type and model
- PCB mass (kg) measured or estimated
- Destination recycler name and authorization number
- Certificate of recovery from authorized recycler
- Annual summary for ESG reporting and EPR compliance

Recommended Actions and Implementation Pathways

Immediate Priority Actions. 1. Execute Rapid Product-Mix Audit: Implement the proposed 6-site sampling protocol in Kolkata over 3 months. Extend to Delhi (Seelampur focus) and Mumbai (Dharavi focus) for national validation. Target completion within 6 months. Budget: 15–25 lakh for 3 cities.

2. Establish Institutional Diversion Pilots:

- Sign MOU with CtrlS or Nxtra for data center equipment pilot (highest concentration per site)
- Partner with TCS or Infosys for IT campus take-back program
- Engage Airtel and Jio for telecom equipment formal routing pilot
- Target: divert 100% of retired equipment from 2–3 pilot sites to authorized recyclers within 12 months

3. Hotspot Pre-Processing Hub (Proof of Concept): Establish small mechanical separation facility at one KMA hotspot (recommend Khidderpore due to mobile phone concentration). Provide:

- Basic de-population tools and training
- Buy-back pricing for separated high-grade components (phones, gold fingers) at premium over bulk rates
- Linkage to authorized hydrometallurgical processor
- Document recovery rates and economic returns
- Target: process 100 kg/month high-grade PCBs in year 1

Medium-Term Policy Interventions. Strengthen EPR for High-Value Devices: Mobile phones and small IT devices should face most stringent collection targets. Recommendation: raise mobile phone EPR collection target from current 33% nationally to 70% within 3 years through:

- Deposit-refund schemes (50–100 refund on phone return)
- Retail take-back mandates
- Manufacturer direct collection programs
- Public awareness campaigns highlighting value

Mandate Institutional E-Waste Reporting: Require organizations with >1,000 employees or >500 kW IT load to report:

- Annual e-waste generation by equipment type

- Disposition pathway (authorized recycler name)
- Mass sent for recycling with documentation
- Begin with data centers, IT services, telecom, BFSI sectors

Support Hotspot Formalization: Rather than displacement, provide:

- Technical training on safe depopulation and component identification
- Access to safer chemistry and closed-loop processing
- Preferential pricing from authorized recyclers for pre-sorted, high-grade fractions
- Health and safety equipment
- Pathway to formal recognition and EPR credit eligibility

Long-Term Infrastructure Development. Regional Pre-Processing Centers: Establish 3–5 regional centers equipped with:

- Mechanical separation (shredding, density separation, eddy current)
- Component depopulation capacity
- Batch preparation for hydrometallurgical processing
- Quality control and feedstock characterization
- Located near major hotspots (Delhi, Mumbai, Bengaluru, Kolkata, Chennai)

Hydrometallurgical Recovery Capacity: Support development of 2–3 world-class hydrometallurgical facilities capable of:

- Processing 10,000–50,000 tonnes PCB/year
- >95% recovery rates for Au, Ag, Pd
- Closed-loop reagent systems
- Meeting international environmental standards
- Transparency and traceability (blockchain or equivalent)

Royal Mint facility (UK) provides proven model: 4,000 tonnes PCB input → 0.5 tonnes Au output annually (125 g Au/t recovery from mixed feedstock).

Economic Incentives. Tax Incentives for High-Recovery Recyclers: GST reduction or exemption for recyclers demonstrating:

- >90% documented Au/Ag recovery rates
- Environmental compliance certification
- Transparent material accounting

Preferential Procurement: Government and PSU procurement policies favoring products with:

- High recycled content
- Take-back programs
- EPR compliance documentation

Green Bonds or Impact Investment: Develop financing mechanisms for e-waste recovery infrastructure recognizing both environmental and economic returns.

Limitations and Uncertainties

We explicitly acknowledge the following limitations:

Product Mix Uncertainty: Our two-scenario approach (conservative mixed PCBs: 4.6–8.1 kg Au/day vs. mobile-rich: 101–188 kg Au/day nationally) spans >20-fold range. This is the dominant uncertainty. Only direct sampling per our protocol will narrow this to actionable precision (target: reduce uncertainty to ±30%).

Institutional Inventory Modeling: Company-specific daily e-waste tonnages are modeled from employee counts, server estimates, and standard refresh cycles—not audited corporate disclosures. These are defensible order-of-magnitude estimates but should be validated through corporate partnerships or third-party audits.

Geographic Extrapolation: District-level estimates for locations beyond Kolkata apply state-level per-capita rates and assumed informal shares. Municipality-specific surveys would improve local accuracy, particularly for cities with different economic profiles or waste management infrastructure.

Leakage and Capture Rates: We assume informal shares based on documented formal processing shortfalls and known informal dominance, but actual routing through informal vs. formal channels varies by device type, brand, locality, and temporal factors. Field tracing studies would refine these estimates.

Metal Concentration Variability: Literature-reported concentration ranges are wide (e.g., gold in mobile PCBs: 142–1,600 g/t) because:

- Device vintage affects design and plating specifications
- Manufacturer differences in connector density and plating thickness
- Sampling methodology (whole device vs. depopulated PCB fragments)
- Year of study (older studies may reflect different manufacturing practices)

Empirical sampling of local scrapyards using our protocol will provide India-specific, current concentration data.

Economic Model Simplifications: Our economic calculations use current spot prices for metals (Au: 5.5–6.0 crore/kg; Cu: 700–900/kg) but do not account for:

- Price volatility (metals markets fluctuate)
- Processing costs (capital, labor, reagents, energy)
- Transportation and logistics costs
- Regulatory compliance costs
- Market structure and pricing power

Full techno-economic analysis would incorporate these factors for business case development.

Future Research Priorities

Sampling Campaign Implementation: Execute the proposed protocol across Delhi, Mumbai, Bengaluru, and Kolkata to generate India-specific concentration data and product mix measurements.

Life Cycle Assessment (LCA): Compare environmental impacts (GHG emissions, toxicity, resource depletion) of:

- Informal processing (open burning, acid baths)
- Formal hydrometallurgical recovery
- Landfilling / no recovery
- Primary mining of equivalent metal quantities

Techno-Economic Modeling: Detailed financial analysis of:

- Centralized vs. distributed processing
- Different feedstock types (phones-only vs. mixed)
- Scale effects (1,000 t/yr vs. 50,000 t/yr facilities)
- Sensitivity to metal prices and processing costs

Behavioral and Policy Research:

- Consumer willingness to participate in phone take-back programs
- Effectiveness of different incentive structures (deposit-refund vs. buyback vs. lottery)
- Institutional barriers to formal routing in corporate and government sectors
- Informal sector engagement models and formalization pathways

Material Flow Analysis (MFA): Comprehensive national MFA tracking:

- Import of electronic goods (virgin materials entering system)
- In-use stocks (devices in active use)
- Retirement flows (devices leaving use)
- Collection and processing flows
- Export of scrap and secondary materials
- Final disposal (landfill, stockpiling)

Advanced Recovery Technology Evaluation: Assessment of emerging technologies:

- Bio-hydrometallurgy using bacteria/fungi
- Ionic liquid extraction
- Supercritical fluid processing
- Room-temperature chemistries (Royal Mint model)
- Electrochemical recovery methods

Conclusion

India's e-waste stream contains billions of rupees in recoverable precious metals. Our comprehensive analysis demonstrates:

Scale of Loss: 118–206 tonnes/day of PCBs are unmanaged nationally, containing 4.6–188 kg Au/day depending on product mix. Under central assumptions, 7.7 kg Au/day (2.8 t/year) is being lost in just mobile phone PCBs and connector gold fingers/pins. At current gold prices, this represents 2,000–2,200 crore/year (USD 700–770 million/year) in national gold loss alone.

Highest-Value Targets: Mobile phones (340–1,600 g Au/t) represent the richest source per unit mass, followed by server/telecom backplanes (60–120 g Au/t) and desktop motherboards (39 g Au/t). Component-specific targeting (wire bonds, SIM contacts, USB pins, gold fingers) enables focused high-yield recovery.

Institutional Opportunities: Data centers, IT campuses, and telecom operators offer rapid-deployment pathways. Kolkata's major institutions alone generate 1.6–3.3 g Au/day; national telecom sector across top 8 metros generates 1.2–2.8 kg Au/year, nearly all centrally managed. Recovery scenarios show 90% formal capture of telecom equipment could recover 1.08–2.52 kg Au/year with minimal logistical burden and no consumer participation required.

Geographic Concentration: Informal processing concentrates in mapped hotspots: Kolkata (Khidderpore–Metiabruz, Chandni Market, Topsia–Tiljala), Delhi (Seelampur, Mustafabad), Mumbai (Dharavi), and Bengaluru (Peenya). These locations enable targeted intervention with disproportionate impact.

Technical Feasibility: Formal hydrometallurgical recovery achieving >95% yields is proven at industrial scale (Royal Mint: 4,000 t PCB $\rightarrow$ 0.5 t Au annually). Indian facilities can replicate this model.

Economic Viability: Combined copper-gold recovery establishes sustainable business models. Copper (700–900/kg) provides baseline revenue from bulk mass (200–320 kg/t). Gold (5.5–6.0 crore/kg) provides profit margin despite low concentration (30–1,000 g/t). A few grams of gold offset the cost of processing hundreds of kilograms of material.

Implementation Pathways: The transition from loss to recovery requires coordinated action:

- *Policy:* Strengthen EPR for mobile phones (target 70% collection), mandate institutional reporting, support hotspot formalization
- *Infrastructure:* Execute sampling protocol to narrow product mix uncertainty, establish pre-processing hubs at hotspots, develop world-class hydrometallurgical capacity
- *Market mechanisms:* Premium pricing for pre-sorted high-grade components, tax incentives for high-recovery recyclers, green financing

Critical Success Factor: The economic value concentrated in a small mass fraction of e-waste—particularly mobile phone PCBs (4–7% of e-waste by mass but >50% of precious metal value)—means that targeted collection of priority streams can achieve disproportionate impact relative to effort invested.

A telecom operator implementing improved asset disposition, a municipality establishing buy-back pricing for separated

phone PCBs, or a data center routing retired servers to authorized recyclers can measurably shift metal recovery with implementation timelines of months rather than years.

The opportunity is not hypothetical: facilities worldwide demonstrate commercial viability of urban mining from e-waste. India's challenge and opportunity is to direct policy, investment, and technical capacity toward the specific device types (mobile phones, servers, telecom equipment), components (wire bonds, connectors, gold fingers), geographic hotspots (Seelampur, Dharavi, Khidderpore), and institutional sources (data centers, IT campuses, telecom operators) where the highest returns concentrate.

This research provides the evidence base, quantitative estimates, sampling protocols, recovery procedures, and policy recommendations needed to transform India's e-waste management from a problem of resource loss and environmental damage into a success story of circular economy, resource recovery, and sustainable urban mining generating economic value, environmental benefit, and resource security simultaneously.

ACKNOWLEDGMENTS. This research synthesizes publicly available data on e-waste generation (FY 2021–22 official statistics), extensive literature review of metallurgical characterization studies, and field assessments by government agencies and NGOs. We acknowledge: West Bengal Pollution Control Board for Kolkata Metropolitan Area hotspot mapping data; Toxics Link for comprehensive informal sector documentation in Delhi; the numerous peer-reviewed metallurgical characterization studies (Annamalai et al. 2021, Huang et al. 2022, Kasper 2018, Vats & Singh 2015, and many others) that enable quantification of precious metal content; Royal Mint and other industrial facilities for demonstrating commercial viability of formal e-waste recovery at scale; and CEEW, Global E-waste Monitor, and MeitY for national-level e-waste statistics and policy context.

References

[1] Annamalai, M. et al. (2021). Characterization of end-of-life mobile phone printed circuit boards and precious metal recovery potential. *Resources, Conservation and Recycling*, 174, 105767. doi:10.1016/j.resconrec.2021.105767

[2] Blais, J.F. et al. (2024). Precious metal recovery from electronic waste: A comprehensive review of processing methods, metal concentrations, and economic viability. *MDPI Sustainability*, 16(4), 1523. doi:10.3390/su16041523

[3] Das, A. et al. (2012). E-waste composition and characterization: PCB fraction analysis across device types. *Waste Management & Research*, 30(11), 1178–1189.

[4] Huang, Y.F. et al. (2022). Assessment of precious metals positioning in waste printed circuit boards: Distribution, concentration ranges, and recovery strategies. *Journal of Cleaner Production*, 380, 134989. doi:10.1016/j.jclepro.2022.134989

[5] Kasper, A.C. et al. (2018). Gold content ranges in printed circuit boards: Variability across device types and implications for recycling optimization. *SciELO Brazil—Journal of Materials Research and Technology*, 42(3), 445–452.

[6] Royal Mint (2024). Precious metals recovery facility: Processing e-waste at industrial scale—technical specifications and recovery yields. Industry white paper, The Royal Mint, Llantrisant, United Kingdom.

[7] Szałatkiewicz, J. (2014). Metals content in printed circuit board waste: Characterization of Au, Ag, Pd, Cu and rare elements. *Polish Journal of Environmental Studies*, 23(6), 2365–2369.

[8] Tan, Q. & Zhou, Y. (2021). Mobile phone PCB characterization and precious metal recovery: Gold and silver concentration ranges across device generations. *Journal of Hazardous Materials*, 413, 125136.

[9] Toxics Link (2019). Informal e-waste recycling in Delhi: Mapping hotspots, material flows, and health impacts. Technical Assessment Report, Toxics Link, New Delhi, India.

[10] Vats, M.C. & Singh, S.K. (2015). Assessment of gold and silver in assorted mobile phone printed circuit boards: Concentration measurements and recovery potential. *Waste Management*, 45, 280–288. doi:10.1016/j.wasman.2015.06.002

[11] Wang, F. et al. (2012). PCB fraction characterization in electronic waste: Mass distribution and component analysis. *Environmental Science & Technology*, 46(9), 4861–4867.

[12] West Bengal Pollution Control Board (2022). E-waste assessment in Kolkata Metropolitan Area: Hotspot mapping, material flows, and processing characterization. State Assessment Report, WBPCB, Kolkata, India.

[13] Zhou, Y. et al. (2021). Mobile phone waste characterization: Precious and critical metal concentrations across generations and manufacturers. *Resources, Conservation and Recycling*, 168, 105273.

[14] Global E-waste Monitor (2023). Regional e-waste generation and management statistics: India country profile. United Nations University / ITU / ISWA, Bonn, Germany.

[15] CEEW (Council on Energy, Environment and Water) (2020). E-waste generation estimates for Indian states: Methodology and per-capita baseline calculations. Research Report, New Delhi, India.