CARBON BLACK TESTER

DESCRIPTION

Statutory standards prescribe the verification of carbon black content of polyolefin plastics. The test method isbased on pyrolitic decomposition of the material in an inert gas flow (nitrogen). This means that the remaining quantity is burned once again under forced ventilation at the same temperature and the carbon black content determined by means of weight difference.

Simple and safe operation

- Complete test structure compactly assembled
- Overtemperature protection integrated in the tubular furnace

Reliable test results

- Precise temperature control via digital temperature controller

Lasting efficiency

- High-quality unit components guarantee a long service life

Accessories



CARBON BLACK TESTER

Standards	
ISO 6964	
ASTM D 1603	

Versions

		T041V1P
Furnace temperature range	°C	0 – 1000
Furnace accuracy		Up to 200 °C: 0.1 K Above 200 °C: 1 K
Carbon black tester accuracy		Up to 100 °C: 0.1% (±2 digits) Above 100 °C: 0.5 % (±2 digits)
Flow measuring device		5-95 Nl/h or 1-13 Nl/h
Power requirement of tubular furnace	kW	1
CE conformity		●
Permissible ambient temperature	°C	+5 to +30
Permissible relative humidity		Max. 70%, non-condensing
Width	mm	760
Depth	mm	650
Height	mm	1020
Weight	kg	Approx. 60
Voltage data		**1 ph 230 V, 50/60 Hz (other voltages on request)**

● included ○ available / optional □ eligible - not available

POLİNAR PLASTİK MAKİNE ve KALIP SANAYİ
TİCARET LİMİTED ŞİRKETİ
İkitelli O.S.B Eskoop San. Sit. D Blok
No: 34 Başakşehir / İSTANBUL - TURKEY

Phone : +90 212 549 88 20 – 21
Fax : +90 212 549 88 19
E-Mail : info@polinar.com.tr

www.polinar.com.tr

PTE (POLİNAR TEST EQUIPMENT)
İkitelli O.S.B. Eskoop San. Sit.
D Blok No.34 Başakşehir
İstanbul / TURKEY

Phone : +90 212 549 88 20 – 21
Fax : +90 212 549 88 19
E-Mail : info@polinar.com.tr

www.pte.com.tr

POLINAR GmbH
THE ICON VIENNA, Tower 24
Wiedner Gürtel 13 1100
Vienna AUSTRIA

Phone : +43 (0) 1 253535 4044
Fax : +43 (0) 1 253535 4044
Mobile : +43 676 5983869
E-Mail : office@polinar.at

www.polinar.at