ZHEJIANG FURUIDA FOAM CO. LTD

TANGPU INDUSTRIAL ZONE, ANJI ZHEJIANG

Sample Description: FOAM

Color: GREY

Style/Item No.: /

The above sample(s) was / were submitted and identified on behalf of the client. SGS is not responsible for the authenticity, integrity and results of the data and information and / or the validity of the conclusion arising therefrom. Results apply to the sample as received.

****

Test Requested:

The Furniture and Furnishings (Fire) (Safety) Regulations 1988 S.I. No. 1324 (amended 1989, 1993 and 2010), Schedule 1 Part I Ignitability test for foam in slab or cushion form.

As specified in above standard(s) and incorporated with using ignition source 5 of BS 5852 Part 2:1982.

Test Results: -- See attached sheet --

Conclusion: The tested sample **meets** the requirements of Schedule 1 Part I in Statutory Instrument 1988 No. 1324 (Amended 1989, 1993 and 2010) the Furniture and Furnishings (Fire) (Safety) Regulations.

Test Period:

Sample Receiving Date	:	DEC.05, 2022
Test Performing Date	:	DEC.05, 2022 TO DEC.09, 2022

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Anji Branch

Echo Li
Approved Signatory

scan to see the report
AJFS2212009825FF

SGS-CSTC Standards Technical Services Co., Ltd. Anji Branch Fire Technology Service

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编:313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

Member of the SGS Group (SGS SA)

Test Conducted

The Furniture and Furnishings (Fire) (Safety) Regulations 1988 S.I. No. 1324 (amended 1989,1993 and 2010), Schedule 1 Part I Ignitability test for foam in slab or cushion form.

Crib 5 test (Ignition Source 5) of BS 5852 Part 2:1982.

Conditioning

The cribs and specimens were conditioned for 72 h in indoor ambient conditions and then immediately before the test for at least 16 h in an atmosphere having a temperature of 20±5°C and a relative humidity of 50±20%.

At time of testing: Temperature between 15°C ~ 30°C and Relative humidity between 20% ~ 70%.

Test Result

The following test results relate only to the ignitability of the combination of materials under the particular condition of test. They are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

(A) Progressive smouldering

Criteria of failure (Clause 4.1 of BS 5852 Part 2:1982)	1st	2nd
4.1 b) Any composite that product externally detectable amounts of smoke, heat or glow 60 min after ignition of the crib.	No	No
4.1 c) Any composite that displays escalating combustion behaviour so that it is unsafe to continue the test and requires forcible extinction.	No	No
4.1 d) Any composite that smoulders until it is essentially consumed within the test duration relevant to the source.	No	No
4.1 e) Any composite that smoulders to the extremities of the specimen viz. upper or lower margins, either side or to its full thickness, within the duration of the test.	No	No
4.1 f) Any composite that, on the final examination, shows evidence of charring other than discolouration, more than 100 mm in any direction apart from upwards from the nearest part of the original position of the source.	No	No

(B) Flaming

Criteria of failure (Clause 4.2 of BS 5852 Part 2:1982)	1st	2nd
4.2 b) Any composite that continues to flame for more than 10 minutes after the ignition of the crib.	No	No
4.2 d) Any composite that displays escalating combustion behaviour so that it is unsafe to continue the test and forcible extinction is required.	No	No
4.2 e) Any composite that burns until it is essentially consumed within the test duration relevant to the source.	No	No
4.2 f) Any composite on which any flame front reaches the lower margin, either side or passes through the full thickness of the specimen within the duration of the test.	No	No

SGS-CSTC Standards Technical Services Co., Ltd. Anji Branch Fire Technology Service
检验检测专用章 Inspection & Testing Services

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 8307 1443, or email: CN.Doccheck@sgs.com
No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编:313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com
Member of the SGS Group (SGS SA)

(C) Mass Loss

Criteria (Clause 5 in Schedule 1 of UK Regulations)	1st	2nd
If failure against the criteria of clause 4 of BS 5852: Part 2 has occurred but only by way of damage exceeding the limits defined in clause 4.1(e), 4.1(f) and 4.2(f) and provided that the resultant mass loss is less than 60g the foam passes the ignitability test.	28 g	31 g

Result Details:

Test No.		1st	2nd
Progressive smouldering (PS) or Flaming (F)		No	No
Duration of	Ignition source (min, s)	2 min 14 s	2 min 17 s
	Flames (min, s)	3 min 09 s	3 min 25 s
	Smoke (min, s)	3 min 56 s	4 min 11 s
Extent of damage of horizontal component	Foam - Width (mm)	113	118
	Foam - Length (mm)	148	142
	Foam - Depth (mm)	62	65
Extent of damage of vertical component	Foam - Width (mm)	146	152
	Foam - Depth (mm)	57	61
Damage exceeds limits of clauses 4.1(e), 4.1(f) or 4.2(f)		No	No
Initial weight before test (g)		5928	5939
Finial weight after test (g)		5900	5908
Resultant mass loss (g)		28	31
Reason for failure (Ref to failure code)		---	---
Finial examination of progressive smouldering (9.4)		No	No
Comments & observations		No	No
Overall result		Pass	Pass

Statement:

The decision rules for statements of conformity (Pass/Fail) have been applied to any results that results in a numerical value and are based on the Probability Confidence of 95% (UKAS LAB 48) agreed with the customer at the contract review stage.

SGS-CSTC Standards Technical Services Co., Ltd. Anji Branch Fire Technology Service

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 8307 1443, or email: CN.Doccheck@sgs.com
No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编:313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com
Member of the SGS Group (SGS SA)

Photo Appendix:

Details of sample:

Color: Grey

This foam sample of approximate density of 27.3 kg/m^3.



SGS authenticate the photo on original report only

*** End of Report ***

SGS-CSTC Standards Technical Services Co., Ltd. Anji Branch Fire Technology Service

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn

中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编:313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

Member of the SGS Group (SGS SA)