ALUMINUM

6061

MATERIAL / REFERENCE CONDITION

T6 · T651

Typical applications Machined housings, fixtures and mounting plates.

Reference product form	Sheet & plate
Data notes	T6/T651 typical values: tensile 310 MPa; yield 276 MPa; Brinell hardness 95. Typical data, not guaranteed acceptance limits.

Original technical reference | Kaiser Aluminum · external reference

View 6061 data sheet (PDF)

online.kaiseraluminum.com | External publisher; reference only

Selection reference, not a material certificate or guaranteed purchasing specification. Properties apply only to the stated grade, form, condition and test method. Branded examples do not establish Metalcorex stock or supplier identity. Confirm the production specification, supplier sheet and required records with your quotation.