ENGINEERING PLASTICS

PC

MATERIAL / REFERENCE CONDITION

Polycarbonate

Typical applications Transparent covers and impact-resistant housings

Material type	Polycarbonate
Condition / reference grade	Makrolon 2805 (example)
Manufacturing	Machining or molding; confirm grade-specific route
Reference data	Example MVR: 9 cm3/10 min at 300°C / 1.2 kg, ISO 1133-1.
Specification notes	MVR is a processing property, not a mechanical-strength value. Branded examples are references, not a statement of stocked brand.

Original technical reference | Covestro

Manufacturer grade reference

solutions.covestro.com | External publisher; reference only

Selection reference, not a material certificate or guaranteed purchasing specification. Properties apply only to the stated grade, form, condition and test method. Branded examples do not establish Metalcorex stock or supplier identity. Confirm the production specification, supplier sheet and required records with your quotation.