ENGINEERING PLASTICS

PE

MATERIAL / REFERENCE CONDITION

Polyethylene

Typical applications Guides, protective blocks and fabricated parts

Material type	Polyethylene
Condition / reference grade	TECAFINE PE300 natural (example)
Manufacturing	Machining or molding; confirm grade-specific route
Reference data	Example HDPE density: 0.96 g/cm3; tensile modulus 1100 MPa, DIN EN ISO 527-1.
Specification notes	HDPE, LDPE and UHMW-PE are different selections; do not apply this sheet to all PE. Branded examples are references, not a statement of stocked brand.

Original technical reference | Ensinger

Manufacturer grade reference

www.ensinger-online.com | External publisher; reference only

Selection reference, not a material certificate or guaranteed purchasing specification. Properties apply only to the stated grade, form, condition and test method. Branded examples do not establish Metalcorex stock or supplier identity. Confirm the production specification, supplier sheet and required records with your quotation.