CARBON & ALLOY STEEL

# Q355B

## MATERIAL / REFERENCE CONDITION

Low-alloy structural steel

**Typical applications** Load-bearing frames and fabricated supports

| | |
|---|---|
| **Material type** | Low-alloy structural steel |
| **Condition / reference grade** | Hot rolled; specify thickness |
| **Manufacturing** | Cutting · welding · machining |
| **Reference data** | Shougang hot-rolled reference, thickness <= 16 mm: yield >= 355 MPa; tensile 470-630 MPa. |
| **Specification notes** | For thicker sections use the applicable source row; do not treat Q345B as an automatic substitute. |

**Original technical reference** | Shougang

Mill handbook (PDF)

www.shougang.com.cn | External publisher; reference only

Selection reference, not a material certificate or guaranteed purchasing specification. Properties apply only to the stated grade, form, condition and test method. Branded examples do not establish Metalcorex stock or supplier identity. Confirm the production specification, supplier sheet and required records with your quotation.